

PART 1 - GENERAL

- 1.1 RELATED SECTIONS
- .1 Section: 32 11 20 - Granular Base.
  - .2 Section: 32 12 17 - Asphaltic Concrete Paving.

PART 2 - PRODUCTS

- 2.1 MATERIALS
- .1 Granular B Type II: to Ontario Provincial Standard Specification 1010. Maximum size Granular B Type 2, 26.5 mm.

PART 3 - EXECUTION

- 3.1 PLACING
- .1 Place on a clean surface, properly shaped and compacted and free from snow or ice.
  - .2 Place material in layers not exceeding 150 mm when compacted.
  - .3 Spread each layer uniformly using approved grading equipment and methods.
- 3.2 COMPACTING
- .1 Compact each layer to minimum 100% Standard Proctor Density.
  - .2 Add water as required to maintain material at or near optimum moisture content while compacting.
- 3.3 FINISHING
- .1 Finish compacted surface to within 12 mm of established grade as indicated by a 3 m straightedge placed in any direction
  - .2 Correct irregularities greater than 12 mm by loosening the surface and adding or removing material until surface is within specified tolerance.
-

3.4 FIELD QUALITY  
CONTROL

- .1 The Contractor will perform field and laboratory tests for control of moisture, Density (compaction) and aggregate gradation. Results will control Contractor's operations.
- .2 Testing shall be carried out by an independent testing agency, acceptable to the Departmental Representative.