

**Part 1 General****1.1 REFERENCES**

- .1 ASTM International
  - .1 ASTM C117- 04, Standard Test Methods for Material Finer Than 0.075 mm Sieve in Mineral Aggregates by Washing.
  - .2 ASTM C131- 06, Standard Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine.
  - .3 ASTM C136- 06, Standard Test Method for Sieve Analysis of Fine and Coarse Aggregates.
  - .4 ASTM D422- 63(2007), Standard Test Method for Particle-Size Analysis of Soils.
  - .5 ASTM D698- 07e1, Standard Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400ft-lbf/ft<sup>3</sup>) (600kN-m/m<sup>3</sup>).
  - .6 ASTM D1557- 09, Standard Test Method for Laboratory Compaction Characteristics of Soil Using Modified Effort (56,000ft-lbf/ft<sup>3</sup>) (2,700kN-m/m<sup>3</sup>).
  - .7 ASTM D1883- 07e2, Standard Test Method for CBR (California Bearing Ratio) of Laboratory Compacted Soils.
  - .8 ASTM D4318- 10, Standard Test Methods for Liquid Limit, Plastic Limit and Plasticity Index of Soils.
- .2 Canadian General Standards Board (CGSB)
  - .1 CAN/CGSB-8.1- 88, Sieves, Testing, Woven Wire, Inch Series.
  - .2 CAN/CGSB-8.2- M88, Sieves, Testing, Woven Wire, Metric.

**1.2 ACTION AND INFORMATIONAL SUBMITTALS**

- .1 Submit in accordance with Section 01 33 00 - Submittal Procedures.

**1.3 DELIVERY, STORAGE AND HANDLING**

- .1 Deliver, store and handle materials in accordance with Section 01 61 00 - Common Product Requirements.
- .2 Storage and Handling Requirements:
  - .1 Store materials in accordance with erosion and sedimentation control plan.
  - .2 Replace defective or damaged materials with new.

**Part 2 Products****2.1 MATERIALS**

- .1 Granular sub-base material: in accordance with Section 31 05 16 - Aggregate Materials and following requirements:
  - .1 Crushed, pit run or screened stone, gravel or sand.

- .2 Gradations to be within limits specified when tested to ASTM C136 and ASTM C117. Sieve sizes to CAN/CGSB-8.1 CAN/CGSB-8.2.

- .3 Table

Sieve Designation	% Passing			
100 mm	-	-	-	-
75 mm	100	100	100	-
50 mm	-	-	-	100
37.5 mm	-	-	-	-
25 mm	55-100	-	-	60-100
19 mm	-	-	-	-
12.5 mm	-	-	-	38-70
9.5 mm	-	-	-	-
4.75 mm	25-100	25-85	-	22-55
2.00 mm	15-80	-	-	13-42
0.425 mm	4-50	5-30	0-30	5-28
0.180 mm	-	-	-	-
0.075 mm	0-8	0-10	0-8	2-10

- .4 Other properties as follows:
- .1 Liquid Limit: to ASTM D4318, Maximum 25.
  - .2 Plasticity Index: to ASTM D4318, Maximum 6.
  - .3 Los Angeles degradation: to ASTM C131.
    - .1 Maximum loss by mass: 40 %.
  - .4 Particles smaller than 0.02 mm: to ASTM D422, Maximum 3%.
  - .5 Soaked CBR: to ASTM D1883, Minimum 40 when compacted to 100% of ASTM D1557.

## Part 3 Execution

### 3.1 EXAMINATION

- .1 Verification of Conditions: verify conditions of substrate previously installed under other Sections or Contracts are acceptable for granular sub-base installation in accordance with manufacturer's written instructions.
  - .1 Visually inspect substrate in presence of Departmental Representative.
  - .2 Inform Departmental Representative of unacceptable conditions immediately upon discovery.
  - .3 Proceed with installation only after unacceptable conditions have been remedied and after receipt of approval to proceed from Departmental Representative.

---

**3.2 PREPARATION**

- .1 Temporary Erosion and Sedimentation Control:
  - .1 Provide temporary erosion and sedimentation control measures to prevent soil erosion and discharge of soil-bearing water runoff or airborne dust to adjacent properties and walkways, according to sediment and erosion control drawings as well as sediment and erosion control plan, specific to site, that complies with requirements of authorities having jurisdiction.
  - .2 Inspect, repair, and maintain erosion and sedimentation control measures during construction until permanent vegetation has been established.
  - .3 Remove erosion and sedimentation controls and restore and stabilize areas disturbed during removal.

**3.3 PLACING**

- .1 Place granular sub-base after subgrade is inspected and approved by Departmental Representative.
- .2 Construct granular sub-base to depth and grade in areas indicated.
- .3 Ensure no frozen material is placed.
- .4 Place material only on clean unfrozen surface, free from snow or ice.
- .5 Begin spreading sub-base material on crown line or high side of one-way slope.
- .6 Place granular sub-base materials using methods which do not lead to segregation or degradation.
- .7 For spreading and shaping material, use spreader boxes having adjustable templates or screeds which will place material in uniform layers of required thickness.
- .8 Place material to full width in uniform layers not exceeding 150 mm compacted thickness.
  - .1 Departmental Representative may authorize thicker lifts if specified compaction can be achieved.
- .9 Shape each layer to smooth contour and compact to specified density before succeeding layer is placed.
- .10 Remove and replace portion of layer in which material has become segregated during spreading.

**3.4 COMPACTION**

- .1 Compaction equipment to be capable of obtaining required material densities.
- .2 Efficiency of equipment not specified to be proved at least as efficient as specified equipment at no extra cost and written approval must be received from Departmental Representative before use.
- .3 Compact to density of not less than 100 % maximum dry density in accordance with ASTM D698.
- .4 Shape and roll alternately to obtain smooth, even and uniformly compacted sub-base.
- .5 Apply water as necessary during compaction to obtain specified density.

- .6 In areas not accessible to rolling equipment, compact to specified density with mechanical tampers approved by Departmental Representative.
- .7 Correct surface irregularities by loosening and adding or removing material until surface is within specified tolerance.

### **3.5 PROOF ROLLING**

- .1 For proof rolling use standard roller of 45400 kg gross mass with four pneumatic tires each carrying 11350 kg and inflated to 620 kPa. Four tires arranged abreast with centre to centre spacing of 730 mm maximum.
- .2 Where proof rolling reveals areas of defective sub-base, remove and replace in accordance with this section at no extra cost.

### **3.6 CLEANING**

- .1 Progress Cleaning: clean in accordance with Section 01 74 11 - Cleaning.
  - .1 Leave Work area clean at end of each day.
- .2 Final Cleaning: upon completion remove surplus materials, rubbish, tools and equipment in accordance with Section 01 74 11 - Cleaning.

### **3.7 SITE TOLERANCES**

- .1 Finished sub-base surface to be within 10 mm of elevation as indicated but not uniformly high or low.

### **3.8 PROTECTION**

- .1 Maintain finished sub-base in condition conforming to this section until succeeding base is constructed, or until granular sub-base is accepted by Departmental Representative.

**END OF SECTION**