

PART 1        GENERAL

- |   |    |   |
|---|----|---|
| <u>1.1    REFERENCES</u>                    | .1 | American Society for Testing and Materials International, (ASTM).   |
|   | .1 | ASTM C645-00, Specification for Nonstructural Steel Framing Members.  |
|   | .2 | ASTM C754-00, Specification for Installation of Steel Framing Members to Receive Screw-Attached Gypsum Panel Products.  |
|   | .2 | Canadian General Standards Board (CGSB).  |
|   | .1 | CAN/CGSB-1.40-97, Primer, Structural Steel, Oil Alkyd Type.   |
|   | .3 | Environmental Choice Program (ECP).   |
|   | .1 | CCD-047a -98, Paints - Surface Coatings.  |
|   | .2 | CCD-048-98, Surface Coatings - Recycled Water-borne.  |
| <u>1.2    QUALITY ASSURANCE</u>             | .1 | Test Reports: certified test reports showing compliance with specified performance characteristics and physical properties.   |
|   | .2 | Certificates: product certificates signed by manufacturer certifying materials comply with specified performance characteristics and criteria and physical requirements.  |
| <u>1.3    WASTE MANAGEMENT AND DISPOSAL</u> | .1 | Separate and recycle waste materials in accordance with Section 01 74 21 - Construction/Demolition Waste Management And Disposal.   |
|   | .2 | Remove from site and dispose of packaging materials at appropriate recycling facilities.  |
|   | .3 | Collect and separate for disposal paper plastic polystyrene corrugated cardboard packaging material in appropriate on-site covered locked steel dumpster containers for recycling in accordance with Waste Management Plan. |
|   | .4 | Divert unused metal materials from landfill to metal recycling facility approved by   |

Departmental Representative.

- .5 Divert unused gypsum materials from landfill to recycling facility approved by Departmental Representative.

## PART 2 PRODUCTS

- |                      |    |  |
|----------------------|----|--|
| <u>2.1 MATERIALS</u> | .1 | Non-load bearing channel stud framing: to ASTM C645, stud size indicated, roll formed from 0.53 mm thickness hot dipped galvanized steel sheet, for screw attachment of gypsum board. Knock-out service holes at 460 mm centres. |
|                      | .2 | Floor and ceiling tracks: to ASTM C645, in widths to suit stud sizes, 32 mm flange height.   |
|                      | .3 | Metal channel stiffener 1.4 mm thick cold rolled steel, coated with rust inhibitive coating.   |
|                      | .4 | Insulating strip: rubberized, moisture resistant 3 mm thick foam strip, 12 mm wide, with self sticking adhesive on one face, lengths as required.  |

## PART 3 EXECUTION

- |                     |    |  |
|---------------------|----|--|
| <u>3.1 ERECTION</u> | .1 | Align partition tracks at floor and ceiling and secure at 600 mm on centre maximum.  |
|                     | .2 | Install damp proof course under stud shoe tracks of partitions on slabs on grade.  |
|                     | .3 | Place studs vertically at 400 mm on centre and not more than 50 mm from abutting walls, and at each side of openings and corners. Position studs in tracks at floor and ceiling. Cross brace steel studs as required to provide rigid installation to manufacturer's instructions. |
|                     | .4 | Erect metal studding to tolerance of 1:1000.   |
|                     | .5 | Attach studs to bottom ceiling track using screws.   |
|                     | .6 | Co-ordinate simultaneous erection of studs   |

with installation of service lines. When erecting studs ensure web openings are aligned.

- .7 Co-ordinate erection of studs with installation of door/window frames and special supports or anchorage for work specified in other Sections.
- .8 Provide two studs extending from floor to ceiling at each side of openings wider than stud centres specified. Secure studs together, 50 mm apart using column clips or other approved means of fastening placed alongside frame anchor clips.
- .9 Install heavy gauge single jamb studs at openings.
- .10 Erect track at head of door/window openings and sills of sidelight/window openings to accommodate intermediate studs. Secure track to studs at each end, in accordance with manufacturer's instructions. Install intermediate studs above and below openings in same manner and spacing as wall studs.
- .11 Frame openings and around built-in equipment, cabinets, access panels, on four sides. Extend framing into reveals. Check clearances with equipment suppliers.
- .12 Provide 40 mm stud or furring channel secured between studs for attachment of fixtures behind lavatory basins, toilet and bathroom accessories, and other fixtures including grab bars and towel rails, attached to steel stud partitions.
- .13 Install steel studs or furring channel between studs for attaching electrical and other boxes.
- .14 Extend partitions to ceiling height except where noted otherwise on drawings.
- .15 Maintain clearance under beams and structural slabs to avoid transmission of structural loads to studs. Use 50 mm leg ceiling tracks. Use double track slip joint.
- .16 Install continuous insulating strips to isolate studs from uninsulated surfaces.

- |            |                 |    |   |
|------------|-----------------|----|---|
| <u>3.2</u> | <u>CLEANING</u> | .1 | Upon completion of installation, remove surplus materials, rubbish, tools and equipment barriers. |
|------------|-----------------|----|---|

PART 1        GENERAL

- |                                 |   |
|---------------------------------|---|
| <u>1.1    REFERENCES</u>        | .1    Environmental Protection Agency (EPA)   |
|                                 | .1    Test Method for Measuring Total Volatile Organic Compound Content of Consumer Products, Method 24 (for Surface Coatings).   |
|                                 | .2    Health Canada/Workplace Hazardous Materials Information System (WHMIS)  |
|                                 | .1    Material Safety Data Sheets (MSDS).   |
|                                 | .3    The Master Painters Institute (MPI)   |
|                                 | .1    Architectural Painting Specification Manual - February 2004.  |
|                                 | .2    Standard GPS-1-05, MPI Green Performance Standard for Painting and Coatings.  |
|                                 | .4    National Fire Code of Canada.   |
|                                 | .5    Society for Protective Coatings (SSPC)  |
|                                 | .1    Systems and Specifications, SSPC Painting Manual 2005.  |
| <u>1.2    QUALITY ASSURANCE</u> | .1    Qualifications:   |
|                                 | .1    Contractor: to have a minimum of five years proven satisfactory experience. When requested, provide list of last three comparable jobs including, job name and location, specifying authority, and project manager. |
|                                 | .2    Qualified journeypersons as defined by local jurisdiction to be engaged in painting work  |
|                                 | .3    Apprentices: may be employed provided they work under direct supervision of qualified journeyperson in accordance with trade regulations.   |
|                                 | .4    Conform to latest MPI requirements for exterior painting work including preparation and priming.  |
|                                 | .5    Materials: in accordance with MPI Painting Specification Manual "Approved Product" listing and from a single manufacturer for each system used.   |
|                                 | .6    Paint materials such as linseed oil, shellac, and turpentine to be highest quality product of an approved   |

manufacturer listed in MPI Painting Specification Manual and to be compatible with other coating materials as required.

- .7 Retain purchase orders, invoices and documents to prove conformance with noted MPI requirements when requested by Departmental Representative Engineer Consultant.

- .8 Standard of Acceptance:

- .1 Final coat to exhibit uniformity of colour and uniformity of sheen across full surface area.

### 1.3 PERFORMANCE REQUIREMENTS

- .1 Environmental Performance Requirements:
  - .1 Provide paint products meeting MPI "Environmentally Friendly" E2 ratings based on VOC (EPA Method 24) content levels.
  - .2 Green Performance in accordance with MPI Standard GPS-1.

### 1.4 SCHEDULING

- .1 Submit work schedule for various stages of painting to Departmental Representative for approval. Submit schedule minimum of 48 hours in advance of proposed operations.
- .2 Obtain written authorization from Departmental Representative for changes in work schedule.
- .3 Schedule painting operations to prevent disruption of occupants in and about building.

### 1.5 SUBMITTALS

- .1 Provide submittals in accordance with Section 01 33 00 - Submittal Procedures.
- .2 Product Data:
  - .1 Submit manufacturer's printed product literature, specifications and datasheet and include product characteristics, performance criteria, physical size, finish and limitations.
  - .2 Submit WHMIS MSDS - Material Safety Data Sheets in accordance with Section 01 10 10 - General Instructions.
- .3 Upon completion, submit records of products

used. List products in relation to finish system and include the following:

- .1 Product name, type and use.
- .2 Manufacturer's product number.
- .3 Colour numbers.
- .4 MPI Environmentally Friendly classification system rating.
- .5 Manufacturer's Material Safety Data Sheets (MSDS).

- .4 Provide samples in accordance with Section 01 33 00 - Submittal Procedures.

- .1 Submit duplicate 200 x 300 mm sample panels of each paint clear coating special finish with specified paint or coating in colours, gloss/sheen and textures required to MPI Painting Specification Manual standards submitted on the following substrate materials:

- .1 3 mm plate steel for finishes over metal surfaces.
- .2 When approved, samples shall become acceptable standard of quality for appropriate on-site surface with one of each sample retained on-site.
- .3 Submit full range of available colours where colour availability is restricted.

#### 1.6 MAINTENANCE

- .1 Extra Materials:
  - .1 Submit maintenance materials in accordance with Section 01 78 00 - Closeout Submittals.
- .2 Submit one; four litre can of each type and colour of primer finish coating. Identify colour and paint type in relation to established colour schedule and finish system.

#### 1.7 DELIVERY, STORAGE AND HANDLING

- .1 Deliver, store and handle materials in accordance with Section 01 61 00 - Common Product Requirements, supplemented as follows:
  - .1 Deliver and store materials in original containers, sealed, with labels intact.
  - .2 Labels: to indicate:
    - .1 Manufacturer's name and address.

- .2 Type of paint or coating.
- .3 Compliance with applicable standard.
- .4 Colour number in accordance with established colour schedule.
- .3 Remove damaged, opened and rejected materials from site.
- .4 Provide and maintain dry, temperature controlled, secure storage.
- .5 Observe manufacturer's recommendations for storage and handling.
- .6 Store materials and supplies away from heat generating devices.
- .7 Store materials and equipment in well-ventilated area with temperature range 7 degrees C to 30 degrees C.
- .8 Store temperature sensitive products above minimum temperature as recommended by manufacturer.
- .9 Keep areas used for storage, cleaning and preparation, clean and orderly to approval of Departmental Representative. After completion of operations, return areas to clean condition to approval of Departmental Representative.
- .10 Remove paint materials from storage only in quantities required for same day use.
- .11 Comply with requirements of Workplace Hazardous Materials Information System (WHMIS) regarding use, handling storage, and disposal of hazardous materials.
- .12 Fire Safety Requirements:
  - .1 Provide one 9 kg Type ABC dry chemical fire extinguisher adjacent to storage area.
  - .2 Store oily rags, waste products, empty containers and materials subject to spontaneous combustion in ULC approved, sealed containers and remove from site on a daily basis.
  - .3 Handle, store, use and dispose of flammable and combustible materials in accordance with the National Fire Code of Canada.
- .2 Waste Management and Disposal:
  - .1 Separate waste materials for reuse and recycling in accordance with Section



- 01 74 21 - Construction/Demolition Waste Management and Disposal.
- .2 Paint, and wood preservative finishes and related materials (thinners, solvents, etc.) are regarded as hazardous products and are subject to regulations for disposal. Information on these controls can be obtained from Provincial Ministries of Environment and Regional levels of Government.
  - .3 Material which cannot be reused must be treated as hazardous waste and disposed of in an appropriate manner.
  - .4 Place materials defined as hazardous or toxic waste, including used sealant and adhesive tubes and containers, in containers or areas designated for hazardous waste.
  - .5 To reduce the amount of contaminants entering waterways, sanitary/storm drain systems or into the ground the following procedures shall be strictly adhered to:
    - .1 Retain cleaning water for water-based materials to allow sediments to be filtered out.
    - .2 Retain cleaners, thinners, solvents and excess paint and place in designated containers and ensure proper disposal.
    - .3 Return solvent and oil soaked rags used during painting operations for contaminant recovery, proper disposal, or appropriate cleaning and laundering.
    - .4 Dispose of contaminants in an approved legal manner in accordance with hazardous waste regulations.
    - .5 Empty paint cans are to be dry prior to disposal or recycling (where available).
  - .6 Where paint recycling is available, collect waste paint by type and provide for delivery to recycling or collection facility.
  - .7 Set aside and protect surplus and uncontaminated finish materials: Deliver to or arrange collection by employees, individuals, or organizations for verifiable re-use or re-manufacturing.

- .8 Close and seal tightly partly used sealant and adhesive containers and store protected in well ventilated fire-safe area at moderate temperature.

1.8 AMBIENT  
CONDITIONS

---

- .1 Heating, Ventilation and Lighting:
  - .1 Ventilate enclosed spaces in accordance with Section.
  - .2 Do not perform painting work unless adequate and continuous ventilation and sufficient heating facilities are in place to maintain ambient air and substrate temperatures above 10 degrees C for 24 hours before, during and after paint application until paint has cured sufficiently.
  - .3 Where required, provide continuous ventilation for seven days after completion of application of paint.
  - .4 Provide temporary ventilating and heating equipment where permanent facilities are not available or supplemental ventilating and heating equipment if ventilation and heating from existing system is inadequate to meet minimum requirements.
  - .5 Perform no painting work unless a minimum lighting level of 323 Lux is provided on surfaces to be painted. Adequate lighting facilities to be provided by General Contractor.
- .2 Temperature, Humidity and Substrate Moisture Content Levels:
  - .1 Unless specifically pre-approved by Departmental Representative, perform no painting work when:
    - .1 Ambient air and substrate temperatures are below 10 degrees C.
    - .2 Substrate temperature is over 32 degrees C unless paint is specifically formulated for application at high temperatures.
    - .3 Substrate and ambient air temperatures are expected to fall outside MPI or paint manufacturer's prescribed limits.
    - .4 Relative humidity is above 85 % or when dew point is less than 3

- degrees C variance between  
air/surface temperatures.
- .5 Rain or snow are forecast to occur  
before paint has thoroughly cured  
or when it is foggy, misty,  
raining or snowing at site.
- .2 Conduct moisture tests using a properly  
calibrated electronic Moisture Meter,  
except test concrete floors for moisture  
using a simple "cover patch test".
- .3 Test concrete, masonry and plaster  
surfaces for alkalinity as required.
- .3 Surface and Environmental Conditions:
  - .1 Apply paint finish in areas where dust  
is no longer being generated by related  
construction operations or when wind or  
ventilation conditions are such that  
airborne particles will not affect  
quality of finished surface.
  - .2 Apply paint to adequately prepared  
surfaces and to surfaces within moisture  
limits noted herein.
  - .3 Apply paint when previous coat of paint  
is dry or adequately cured.
  - .4 Apply paint finishes when conditions  
forecast for entire period of  
application fall within manufacturer's  
recommendations.
  - .5 Do not apply paint when:
    - .1 Temperature is expected to drop  
below 10 degrees C before paint  
has thoroughly cured.
    - .2 Substrate and ambient air  
temperatures are expected to fall  
outside MPI or paint  
manufacturer's limits.
    - .3 Surface to be painted is wet, damp  
or frosted.
  - .6 Provide and maintain cover when paint  
must be applied in damp or cold weather.  
Heat substrates and surrounding air to  
comply with temperature and humidity  
conditions specified by manufacturer.  
Protect until paint is dry or until  
weather conditions are suitable.
  - .7 Schedule painting operations such that  
surfaces exposed to direct, intense  
sunlight are scheduled for completion  
during early morning.

- .8 Remove paint from areas which have been exposed to freezing, excess humidity, rain, snow or condensation. Prepare surface again and repaint.

## PART 2 PRODUCTS

### 2.1 MATERIALS

- .1 Paint materials listed in latest edition of MPI Approved Products List (APL) are acceptable for use on this project.
- .2 Paint materials for paint systems: to be products of single manufacturer.
- .3 Only qualified products with E2 "Environmentally Friendly" ratings are acceptable for use on this project.
- .4 Use only MPI listed L rated materials.
- .5 Paints, coatings, adhesives, solvents, cleaners, lubricants, and other fluids, to be as follows:
  - .1 Be water soluble water clean-up.
  - .2 Be non-flammable biodegradable.
  - .3 Be manufactured without compounds which contribute to ozone depletion in upper atmosphere.
  - .4 Be manufactured without compounds which contribute to smog in the lower atmosphere.
  - .5 Do not contain methylene chloride, chlorinated hydrocarbons, toxic metal pigments.
  - .6 Have recycled content.
- .6 Water-borne surface coatings must be manufactured and transported in a manner that steps of processes, including disposal of waste products arising therefrom, will meet requirements of applicable governmental acts, by-laws and regulations including, for facilities located in Canada, Fisheries Act and Canadian Environmental Protection Act (CEPA).
- .7 Water-borne surface coatings must not be formulated or manufactured with aromatic solvents, formaldehyde, halogenated solvents, mercury, lead, cadmium, hexavalent chromium

or their compounds.

- .8 Water-borne surface coatings and recycled water-borne surface coatings must have flash point of 61.0 degrees C or greater.
- .9 Both water-borne surface coatings and recycled water-borne surface coatings must be made by a process that does not release:
  - .1 Matter in undiluted production plant effluent generating a 'Biochemical Oxygen Demand' (BOD) in excess of 15 mg/L to a natural watercourse or a sewage treatment facility lacking secondary treatment.
  - .2 Total Suspended Solids (TSS) in undiluted production plant effluent in excess of 15 mg/L to a natural watercourse or a sewage treatment facility lacking secondary treatment.
- .10 Water-borne paints and stains, recycled water-borne surface coatings and water borne varnishes must meet a minimum "Environmentally Friendly" E2 rating.
- .11 Recycled water-borne surface coatings must contain 50 % post-consumer material by volume.
- .12 Recycled water-borne surface coatings must not contain:
  - .1 Lead in excess of 600.0 ppm weight/weight total solids.
  - .2 Mercury in excess of 50.0 ppm weight/weight total product.
  - .3 Cadmium in excess of 1.0 ppm weight/weight total product.
  - .4 Hexavalent chromium in excess of 3.0 ppm weight/weight total product.
  - .5 Organochlorines or polychlorinated biphenyls (PCBS) in excess of 1.0 ppm weight/weight total product.
- .13 The following must be performed on each batch of consolidated post-consumer material before surface coating is reformulated and canned. These tests must be performed at a laboratory or facility which has been accredited by the Standards Council of Canada.
  - .1 Lead, cadmium and chromium are to be

determined using ICP-AES (Inductively Coupled Plasma - Atomic Emission Spectroscopy) technique no. 6010 as defined in EPA SW-846.

.2 Mercury is to be determined by Cold Vapour Atomic Absorption Spectroscopy using Technique no. 7471 as defined in EPA SW-846.

.3 Organochlorines and PCBs are to be determined by Gas Chromatography using Technique no. 8081 as defined in EPA SW-846.

## 2.2 COLOURS

.1 Departmental Representative will provide Colour Schedule after Contract award.

.2 Colour schedule will be based upon selection of two base colours and two accent colours. No more than four colours will be selected for entire project.

.3 Selection of colours will be from manufacturer's full range of colours.

.4 Where specific products are available in restricted range of colours, selection will be based on limited range.

.5 Second coat in three coat system to be tinted slightly lighter colour than top coat to show visible difference between coats.

## 2.3 MIXING AND TINTING

.1 Perform colour tinting operations prior to delivery of paint to site. On-site tinting of painting materials is allowed only with Departmental Representative's written permission.

.2 Mix paste, powder or catalyzed paint mixes in accordance with manufacturer's written instructions.

.3 Add thinner to paint manufacturer's recommendations. Do not use kerosene or organic solvents to thin water-based paints.

.4 Thin paint for spraying according in accordance with paint manufacturer's instructions. If directions are not on container, obtain instructions in writing from manufacturer and provide copy of

instructions to Departmental Representative.

- .5 Re-mix paint in containers prior to and during application to ensure break-up of lumps, complete dispersion of settled pigment, and colour and gloss uniformity.

#### 2.4 GLOSS/SHEEN RATINGS

- .1 Paint gloss: defined as sheen rating of applied paint, in accordance with following values:

Gloss Level Category/	Units @ 60 Degrees/
G1 - matte finish 0 to 5	max. 10
G2 - velvet finish 0 to 10	10 to 35
G3 - eggshell finish 10 to 25	10 to 35
G4 - satin finish 20 to 35	min. 35
G5 - semi-gloss finish	35 to 70
G6 - gloss finish 70 to 85	
G7 - high gloss finish	> 85

- .2 Gloss level ratings of painted surfaces as specified and as noted on Finish Schedule.

#### 2.5 EXTERIOR PAINTING SYSTEMS

- .1 Asphalt Surfaces: zone/traffic marking for drive and parking areas, etc.
  - .1 EXT 2.1A - Latex zone/traffic marking finish.
- .2 Structural Steel and Metal Fabrications:
  - .1 EXT 5.1B - Waterborne light industrial gloss G5 coating (over inorganic zinc).
- .3 Galvanized Metal: not chromate passivated
  - .1 EXT 5.3A - Latex G5 gloss level finish.

### PART 3 EXECUTION

#### 3.1 MANUFACTURER'S INSTRUCTIONS

- .1 Compliance: comply with manufacturer's written recommendations or specifications, including product technical bulletins, handling, storage and installation instructions, and datasheets.

#### 3.2 PREPARATION

- .1 Perform preparation and operations for exterior painting in accordance with MPI Maintenance Repainting Manual except where specified otherwise.

- .2 Apply paint materials in accordance with paint manufacturer's written application instructions.
- .3 Clean and prepare exterior surfaces to be repainted in accordance with MPI Maintenance Repainting Manual requirements. Refer to the MPI Manual in regard to specific requirements and as follows:
  - .1 Remove dust, dirt, and surface debris by vacuuming, wiping with dry, clean cloths or compressed air.
  - .2 Wash surfaces with a biodegradable detergent and bleach where applicable and clean warm water using a stiff bristle brush to remove dirt, oil and other surface contaminants.
  - .3 Rinse scrubbed surfaces with clean water until foreign matter is flushed from surface.
  - .4 Allow surfaces to drain completely and allow to dry thoroughly. Allow sufficient drying time and test surfaces using electronic moisture meter before commencing work.
  - .5 Use water-based cleaners in place of organic solvents where surfaces will be repainted using water based paints.
  - .6 Many water-based paints cannot be removed with water once dried. Minimize use of kerosene or such organic solvents to clean up water-based paints.
- .4 Prevent contamination of cleaned surfaces by salts, acids, alkalis, other corrosive chemicals, grease, oil and solvents before priming and between applications of remaining coats. Touch-up, spot prime, and apply primer, paint, or pretreatment as soon as possible after cleaning and before deterioration occurs.
- .5 Do not apply paint until prepared surfaces have been accepted by Departmental Representative.
- .6 Sand and dust between coats as required to provide adequate adhesion for next coat and to remove defects visible from a distance up to 1000 mm.



- |                                |    |   |
|--------------------------------|----|---|
| <u>3.3 EXISTING CONDITIONS</u> | .1 | Investigate existing substrates for problems related to proper and complete preparation of surfaces to be painted. Report to Departmental Representative damages, defects, unsatisfactory or unfavourable conditions before proceeding with work.   |
|                                | .2 | Conduct moisture testing of surfaces to be painted using a properly calibrated electronic moisture meter, except test concrete floors for moisture using a simple "cover patch test" and report findings to Departmental Representative. Do not proceed with work until conditions fall within acceptable range as recommended by manufacturer. |
| <u>3.4 PROTECTION</u>          | .1 | Protect existing building surfaces and adjacent structures from paint spatters, markings and other damage by suitable non-staining covers or masking. If damaged, clean and restore such surfaces as directed by Departmental Representative.   |
|                                | .2 | Protect items that are permanently attached such as Fire Labels on doors and frames.  |
|                                | .3 | Protect factory finished products and equipment.  |
|                                | .4 | Protect passing pedestrians, and general public in and about building.  |
|                                | .5 | Remove light fixtures, surface hardware on doors, and other surface mounted equipment, fittings and fastenings prior to undertaking painting operations. Store items and re-install after painting is completed.  |
|                                | .6 | Move and cover exterior furniture and portable equipment as necessary to carry out painting operations. Replace as painting operations progress.  |
|                                | .7 | As painting operations progress, place "WET PAINT" signs in pedestrian and vehicle traffic areas to approval of Departmental Representative.  |
| <u>3.5 APPLICATION</u>         | .1 | Method of application to be as approved by Departmental Representative. Apply paint by  |

brush roller air sprayer airless sprayer.  
Conform to manufacturer's application  
instructions unless specified otherwise.

- .2 Brush and Roller Application:
  - .1 Apply paint in a uniform layer using brush and/or roller of types suitable for application.
  - .2 Work paint into cracks, crevices and corners.
  - .3 Paint surfaces and corners not accessible to brush using spray, daubers and/or sheepskins. Paint surfaces and corners not accessible to roller using brush, daubers or sheepskins.
  - .4 Brush and/or roll out runs and sags, and over-lap marks. Rolled surfaces shall be free of roller tracking and heavy stipple unless approved by Departmental Representative.
  - .5 Remove runs, sags and brush marks from finished work and repaint.
- .3 Spray Application:
  - .1 Provide and maintain equipment that is suitable for intended purpose, capable of properly atomizing paint to be applied, and equipped with suitable pressure regulators and gauges.
  - .2 Keep paint ingredients properly mixed in containers during paint application either by continuous mechanical agitation or by intermittent agitation as frequently as necessary.
  - .3 Apply paint in a uniform layer, with overlapping at edges of spray pattern.
  - .4 Brush out immediately runs and sags.
  - .5 Use brushes to work paint into cracks, crevices and places which are not adequately painted by spray.
- .4 Use dipping, sheepskins or daubers when no other method is practical in places of difficult access and when specifically authorized by Departmental Representative.
- .5 Apply coats of paint as continuous film of uniform thickness. Repaint thin spots or bare areas before next coat of paint is applied.

- .6 Allow surfaces to dry and properly cure after cleaning and between subsequent coats for minimum time period as recommended by manufacturer.
- .7 Sand and dust between coats to remove visible defects.
- .8 Finish surfaces both above and below sight lines as specified for surrounding surfaces, including such surfaces as projecting ledges.
- .9 Finish top, bottom, edges and cutouts of doors after fitting as specified for door surfaces.

### 3.6 MECHANICAL/ ELECTRICAL EQUIPMENT

- .1 Unless otherwise specified, paint exterior exposed conduits, piping, hangers, duct work and other mechanical and electrical equipment with colour and finish to match adjacent surfaces, except as noted otherwise.
- .2 Touch up scratches and marks on factory painted finishes and equipment with paint as supplied by manufacturer of equipment.
- .3 Do not paint over nameplates.
- .4 Paint fire protection piping red.
- .5 Paint steel electrical light standards. Do not paint outdoor transformers and substation equipment.

### 3.7 FIELD QUALITY CONTROL

- .1 Inspection:
  - .1 Field inspection of exterior painting operations to be carried out by Departmental Representative.
  - .2 Advise Departmental Representative when each surface and applied coating is ready for inspection. Do not proceed with subsequent coats until previous coat has been approved.
  - .3 Co-operate with Departmental Representative and provide access to areas of work.
- .2 Manufacturer's Field Services:
  - .1 Provide manufacturer's field services consisting of product use

recommendations and periodic site visits for inspection of product installation in accordance with manufacturer's instructions.

- |            |                    |    |  |
|------------|--------------------|----|--|
| <u>3.8</u> | <u>CLEANING</u>    | .1 | Proceed in accordance with Section 01 74 11 - Cleaning.  |
|            |                    | .1 | Remove paint where spilled, splashed, splattered or sprayed as work progresses using means and materials that are not detrimental to affected surfaces.    |
| <u>3.9</u> | <u>RESTORATION</u> | .1 | Clean and re-install hardware items removed before undertaken painting operations.   |
|            |                    | .2 | Remove protective coverings and warning signs as soon as practical after operations cease.   |
|            |                    | .3 | Remove paint splashings on exposed surfaces that were not painted. Remove smears and spatter immediately as operations progress, using compatible solvent. |
|            |                    | .4 | Protect freshly completed surfaces from paint droppings and dust to approval of Departmental Representative. Avoid scuffing newly applied paint.           |
|            |                    | .5 | Restore areas used for storage, cleaning, mixing and handling of paint to clean condition as approved by Departmental Representative.                      |

PART 1        GENERAL

1.1    SUMMARY        .1    Section Includes:

- .1    Material and installation of site applied paint finishes to new interior surfaces, including site painting of shop primed surfaces.

1.2    REFERENCES

- .1    Department of Justice Canada (Jus)
  - .1    Canadian Environmental Protection Act (CEPA), 1999, c. 33
- .2    Environmental Protection Agency (EPA)
  - .1    EPA Test Method for Measuring Total Volatile Organic Compound Content of Consumer Products, Method 24 - 1995, (for Surface Coatings).
- .3    Health Canada / Workplace Hazardous Materials Information System (WHMIS)
  - .1    Material Safety Data Sheets (MSDS).
- .4    Master Painters Institute (MPI)
  - .1    MPI Architectural Painting Specifications Manual, 2004.
- .5    National Fire Code of Canada - 1995
- .6    Society for Protective Coatings (SSPC)
  - .1    SSPC Painting Manual, Volume Two, 8th Edition, Systems and Specifications Manual.
- .7    Transport Canada (TC)
  - .1    Transportation of Dangerous Goods Act (TDGA), 1992, c. 34 .

1.3    QUALITY ASSURANCE

- .1    Qualifications:
  - .1    Contractor: minimum of five years proven satisfactory experience. Provide list of last three comparable jobs including, job name and location, specifying authority, and project manager.
  - .2    Journeymen: qualified journeymen who have "Tradesman Qualification Certificate of Proficiency" engaged in

painting work.

- .3 Apprentices: working under direct supervision of qualified trades person in accordance with trade regulations.

## .2 Health and Safety:

- .1 Do construction occupational health and safety in accordance with Section 01 35 30 - Health and Safety Requirements.

## 1.4 SCHEDULING

- .1 Submit work schedule for various stages of painting to Departmental Representative for review. Submit schedule minimum of 48 hours in advance of proposed operations.
- .2 Obtain written authorization from Departmental Representative for changes in work schedule.
- .3 Schedule painting operations to prevent disruption of occupants.

## 1.5 SUBMITTALS

- .1 Submittals in accordance with Section 01 33 00 - Submittal Procedures.
- .2 Product Data:
  - .1 Submit product data and instructions for each paint and cating product to be used.
  - .2 Submit product data for the use and application of paint thinner.
  - .3 Submit two copies of Workplace Hazardous Materials Information System (WHMIS) Material Safety Data Sheets (MSDS) in accordance with Section 01 33 00 - Submittal Procedures. Indicate VOCs during application and curing.
- .3 Samples:
  - .1 Submit full range colour sample chips to indicate where colour availability is restricted.
  - .2 Submit duplicate 200 x 300 mm sample panels of each paint clear coating with specified paint or coating in colours, gloss/sheen and textures required to MPI Architectural Painting Specification Manual standards submitted on following substrate materials:

- .1 3 mm plate steel for finishes over metal surfaces.
- .3 Retain reviewed samples on-site to demonstrate acceptable standard of quality for appropriate on-site surface.
- .4 Test reports: submit certified test reports for paint from approved independent testing laboratories, indicating compliance with specifications for specified performance characteristics and physical properties.
  - .1 Lead, cadmium and chromium: presence of and amounts.
  - .2 Mercury: presence of and amounts.
  - .3 Organochlorines and PCBs: presence of and amounts.
- .5 Certificates: submit certificates signed by manufacturer certifying that materials comply with specified performance characteristics and physical properties.
- .6 Manufacturer's Instructions:
  - .1 Submit manufacturer's installation and application instructions.
- .7 Closeout Submittals: submit maintenance data for incorporation into manual specified in Section 01 78 00 - Closeout Submittals include following:
  - .1 Product name, type and use.
  - .2 Manufacturer's product number.
  - .3 Colour numbers.
  - .4 MPI Environmentally Friendly classification system rating.

1.6 MAINTENANCE .1

Extra Materials:

- .1 Deliver to extra materials from same production run as products installed. Package products with protective covering and identify with descriptive labels. Comply with Section 01 78 00 - Closeout Submittals.
- .2 Quantity: provide one - four litre can of each type and colour of primer finish coating. Identify colour and paint type in relation to established colour schedule and finish system.
- .3 Delivery, storage and protection: comply with Departmental Representative requirements for delivery and storage of

extra materials.

1.7 DELIVERY,  
STORAGE AND  
HANDLING

- .1 Packing, Shipping, Handling and Unloading:
  - .1 Pack, ship, handle and unload materials in accordance with Section 01 61 00 - Common Product Requirements and manufacturer's written instructions.
- .2 Acceptance at Site:
  - .1 Identify products and materials with labels indicating:
    - .1 Manufacturer's name and address.
    - .2 Type of paint or coating.
    - .3 Compliance with applicable standard.
    - .4 Colour number in accordance with established colour schedule.
- .3 Remove damaged, opened and rejected materials from site.
- .4 Storage and Protection:
  - .1 Provide and maintain dry, temperature controlled, secure storage.
  - .2 Store materials and supplies away from heat generating devices.
  - .3 Store materials and equipment in well-ventilated area with temperature range 7 degrees C to 30 degrees C.
- .5 Store temperature sensitive products above minimum temperature as recommended by manufacturer.
- .6 Keep areas used for storage, cleaning and preparation clean and orderly. After completion of operations, return areas to clean condition.
- .7 Remove paint materials from storage only in quantities required for same day use.
- .8 Fire Safety Requirements:
  - .1 Provide one 9 kg Type ABC dry chemical fire extinguisher adjacent to storage area.
  - .2 Store oily rags, waste products, empty containers and materials subject to spontaneous combustion in ULC approved, sealed containers and remove from site on a daily basis.



- 
- .3 Handle, store, use and dispose of flammable and combustible materials in accordance with National Fire Code of Canada requirements.
  - .9 Waste Management and Disposal:
    - .1 Separate waste materials for recycling in accordance with Section 01 74 21 - Construction/Demolition Waste Management and Disposal .
    - .2 Remove from site and dispose of packaging materials at appropriate recycling facilities.
    - .3 Collect and separate for disposal paper plastic polystyrene corrugated cardboard packaging material in appropriate on-site bins for recycling in accordance with Waste Management Plan (WMP).
    - .4 Separate for recycling and place in designated containers Steel waste in accordance with Waste Management Plan (WMP) .
    - .5 Place materials defined as hazardous or toxic in designated containers.
    - .6 Handle and dispose of hazardous materials in accordance with CEPA, TDGA, Regional and Municipal, regulations.
    - .7 Ensure emptied containers are sealed and stored safely.
    - .8 Unused paint materials must be disposed of at official hazardous material collections site as approved by Departmental Representative.
    - .9 Paint, stain and wood preservative finishes and related materials (thinners, and solvents) are regarded as hazardous products and are subject to regulations for disposal. Information on these controls can be obtained from Provincial Ministries of Environment and Regional levels of Government.
    - .10 Material which cannot be reused must be treated as hazardous waste and disposed of in an appropriate manner.
    - .11 Place materials defined as hazardous or toxic waste, including used sealant and adhesive tubes and containers, in containers or areas designated for hazardous waste.
    - .12 To reduce the amount of contaminants entering waterways, sanitary/storm drain

systems or into ground follow these procedures:

- .1 Retain cleaning water for water-based materials to allow sediments to be filtered out.
- .2 Retain cleaners, thinners, solvents and excess paint and place in designated containers and ensure proper disposal.
- .3 Return solvent and oil soaked rags used during painting operations for contaminant recovery, proper disposal, or appropriate cleaning and laundering.
- .4 Dispose of contaminants in approved legal manner in accordance with hazardous waste regulations.
- .5 Empty paint cans are to be dry prior to disposal or recycling (where available).
- .13 Where paint recycling is available, collect waste paint by type and provide for delivery to recycling or collection facility.
- .14 Set aside and protect surplus and uncontaminated finish materials:  
Deliver to organizations for verifiable re-use or re-manufacturing.

1.8 SITE  
CONDITIONS

- .1 Heating, Ventilation and Lighting:
  - .1 Ventilate enclosed spaces in accordance with Section.
  - .2 Provide heating facilities to maintain ambient air and substrate temperatures above 10 degrees C for 24 hours before, during and after paint application until paint has cured sufficiently.
  - .3 Provide continuous ventilation for seven days after completion of application of paint.
  - .4 Provide temporary ventilating and heating equipment where permanent facilities are not available or supplemental ventilating and heating equipment if ventilation and heating from existing system is inadequate to meet minimum requirements.
  - .5 Provide minimum lighting level of 323 Lux on surfaces to be painted.

.2 Temperature, Humidity and Substrate Moisture Content Levels:

.1 Unless pre-approved written approval by Departmental Representative and product manufacturer, perform no painting when:

- .1 Ambient air and substrate temperatures are below 10 degrees C.
- .2 Substrate temperature is above 32 degrees C unless paint is specifically formulated for application at high temperatures.
- .3 Substrate and ambient air temperatures are not expected to fall within MPI or paint manufacturer's prescribed limits.
- .4 The relative humidity is under 85 % or when the dew point is more than 3 degrees C variance between the air/surface temperatures. Paint should not be applied if the dew point is less than 3 degrees C below the ambient or surface temperature. Use sling psychrometer to establish the relative humidity before beginning paint work.
- .5 Rain or snow are forecast to occur before paint has thoroughly cured or when it is foggy, misty, raining or snowing at site.
- .6 Ensure that conditions are within specified limits during drying or curing process, until newly applied coating can itself withstand 'normal' adverse environmental factors.

.3 Surface and Environmental Conditions:

- .1 Apply paint finish in areas where dust is no longer being generated by related construction operations or when wind or ventilation conditions are such that airborne particles will not affect quality of finished surface.
- .2 Apply paint to adequately prepared surfaces and to surfaces within moisture limits.
- .3 Apply paint when previous coat of paint is dry or adequately cured.

- .4 Additional interior application requirements:
  - .1 Apply paint finishes when temperature at location of installation can be satisfactorily maintained within manufacturer's recommendations.

PART 2 PRODUCTS

2.1 MATERIALS

- .1 Paint materials listed in the MPI Approved Products List (APL) are acceptable for use on this project.
- .2 Provide paint materials for paint systems from single manufacturer.
- .3 Only qualified products with E2 "Environmentally Friendly" rating are acceptable for use on this project.
- .4 Conform to latest MPI requirements for interior painting work including preparation and priming.
- .5 Materials (primers, paints, coatings, fillers, thinners, solvents, etc.) in accordance with MPI Architectural Painting Specification Manual "Approved Product" listing.
- .6 Provide paint products meeting MPI "Environmentally Friendly" E2 ratings based on VOC (EPA Method 24) content levels.
- .7 Use MPI listed materials having minimum E2 rating where indoor air quality (odour) requirements exist.
- .8 Paints, coatings, adhesives, solvents, cleaners, lubricants, and other fluids:
  - .1 Water-based Water soluble Water clean-up .
  - .2 non-flammable biodegradable .
  - .3 Manufactured without compounds which contribute to ozone depletion in the upper atmosphere.
  - .4 Manufactured without compounds which contribute to smog in the lower atmosphere.
  - .5 Do not contain methylene chloride, chlorinated hydrocarbons, toxic metal

pigments.

- .9 Formulate and manufacture water-borne surface coatings with no aromatic solvents, formaldehyde, halogenated solvents, mercury, lead, cadmium, hexavalent chromium or their compounds.
- .10 Flash point: 61.0 degrees C or greater for water-borne surface coatings and recycled water-borne surface coatings.
- .11 Ensure manufacture and process of both water-borne surface coatings and recycled water-borne surface coatings does not release:
  - .1 Matter in undiluted production plant effluent generating 'Biochemical Oxygen Demand' (BOD) in excess of 15 mg/L to natural watercourse or sewage treatment facility lacking secondary treatment.
  - .2 Total Suspended Solids (TSS) in undiluted production plant effluent in excess of 15 mg/L to natural watercourse or a sewage treatment facility lacking secondary treatment.
- .12 Water-borne paints and stains, recycled water-borne surface coatings and water borne varnishes to meet minimum "Environmentally Friendly" E2 rating.
- .13 Recycled water-borne surface coatings to contain 50 % post-consumer material by volume.
- .14 Recycled water-borne surface coatings must not contain:
  - .1 Lead in excess of 600.0 ppm weight/weight total solids.
  - .2 Mercury in excess of 50.0 ppm weight/weight total product.
  - .3 Cadmium in excess of 1.0 ppm weight/weight total product.
  - .4 Hexavalent chromium in excess of 3.0 ppm weight/weight total product.
  - .5 Organochlorines or polychlorinated biphenyls (PCBS) in excess of 1.0 ppm weight/weight total product.

## 2.2 COLOURS

- .1 Departmental Representative will provide Colour Schedule after Contract award.

- .2 Colour schedule will be based upon selection of two base colours and two accent colours. No more than four colours will be selected for entire project.
- .3 Selection of colours from manufacturer's full range of colours.
- .4 Where specific products are available in restricted range of colours, selection based on limited range.
- .5 Second coat in three coat system to be tinted slightly lighter colour than top coat to show visible difference between coats.

### 2.3 MIXING AND TINTING

- .1 Perform colour tinting operations prior to delivery of paint to site. Obtain written approval from Departmental Representative for tinting of painting materials.
- .2 Mix paste, powder or catalyzed paint mixes in accordance with manufacturer's written instructions.
- .3 Use and add thinner in accordance with paint manufacturer's recommendations. Do not use kerosene or similar organic solvents to thin water-based paints.
- .4 Thin paint for spraying in accordance with paint manufacturer's instructions.
- .5 Re-mix paint in containers prior to and during application to ensure break-up of lumps, complete dispersion of settled pigment, and colour and gloss uniformity.

### 2.4 GLOSS/SHEEN RATINGS

- .1 Paint gloss is defined as sheen rating of applied paint, in accordance with following values:

Gloss @ 60 degrees	Sheen @ 85 degrees
Gloss Level 1 - Matte Finish (flat) Max. 5	Max. 10
Gloss Level 2 - Velvet-Like Finish Max.10	10 to 35
Gloss Level 3 - Eggshell Finish 10 to 25	10 to 35
Gloss Level 4 - Satin-Like Finish 20 to 35	min. 35
Gloss Level 5 - Traditional Semi-Gloss Finish	35 to 70
Gloss Level 6 - Traditional Gloss	70 to 85
Gloss Level 7 - High Gloss Finish	More than 85

- .2 Gloss level ratings of painted surfaces as indicated and as noted on Finish Schedule.

## 2.5 INTERIOR PAINTING SYSTEMS

- .1 Structural steel and metal fabrications: columns, beams, joists; decking, girts and frames.
  - .1 INT 5.1B - Waterborne light industrial 65 gloss level coating.
- .2 Galvanized metal: doors, frames, railings, misc. steel, pipes, overhead decking, and ducts.
  - .1 INT 5.3B - Waterborne light industrial 65 gloss level coating.
- .3 Dimension lumber: plywood lumber:
  - .1 INT 6.2A - Latex 65 finish (over alkyd primer).

## 2.6 SOURCE QUALITY CONTROL

- .1 Perform following tests on each batch of consolidated post-consumer material before surface coating is reformulated and canned. Testing by laboratory or facility which has been accredited by Standards Council of Canada.
  - .1 Lead, cadmium and chromium are to be determined using ICP-AES (Inductively Coupled Plasma - Atomic Emission Spectroscopy) technique no. 6010 as defined in EPA SW-846.
  - .2 Mercury is to be determined by Cold Vapour Atomic Absorption Spectroscopy using Technique no. 7471 as defined in EPA SW-846.
  - .3 Organochlorines and PCBs are to be determined by Gas Chromatography using Technique no. 8081 as defined in EPA SW-846.

## PART 3 EXECUTION

### 3.1 MANUFACTURER'S INSTRUCTIONS

- .1 Compliance: comply with manufacturer's written recommendations or specifications, including product technical bulletins, handling, storage and installation instructions, and data sheet.

- 
- |     |                    |    |  |
|-----|--------------------|----|--|
| 3.2 | <u>GENERAL</u>     | .1 | Perform preparation and operations for interior painting in accordance with MPI Architectural Painting Specifications Manual except where specified otherwise.   |
|     |                    | .2 | Apply paint materials in accordance with paint manufacturer's written application instructions.  |
| 3.3 | <u>EXAMINATION</u> | .1 | Investigate existing substrates for problems related to proper and complete preparation of surfaces to be painted. Report to Departmental Representative damages, defects, unsatisfactory or unfavourable conditions before proceeding with work.  |
|     |                    | .2 | Conduct moisture testing of surfaces to be painted using properly calibrated electronic moisture meter, except test concrete floors for moisture using simple "cover patch test". Do not proceed with work until conditions fall within acceptable range as recommended by manufacturer.   |
|     |                    | .3 | Maximum moisture content as follows:<br>.1 Wood: 15 %.   |
| 3.4 | <u>PREPARATION</u> | .1 | Protection:<br>.1 Protect existing building surfaces and adjacent structures from paint spatters, markings and other damage by suitable non-staining covers or masking. If damaged, clean and restore surfaces as directed by Departmental Representative.<br>.2 Protect items that are permanently attached such as Fire Labels on doors and frames.<br>.3 Protect factory finished products and equipment.<br>.4 Protect passing pedestrians, building occupants and general public in and about the building. |
|     |                    | .2 | Surface Preparation:<br>.1 Remove electrical cover plates, light fixtures, surface hardware on doors, bath accessories and other surface mounted equipment, fittings and fastenings prior to undertaking painting operations. Identify and store items in  |



2013-07-06

- 
- secure location and re-installed after painting is completed.
  - .2 Move and cover furniture and portable equipment as necessary to carry out painting operations. Replace as painting operations progress.
  - .3 Place "WET PAINT" signs in occupied areas as painting operations progress. Signs to approval of Departmental Representative Engineer Consultant.
  - .3 Clean and prepare surfaces in accordance with MPI Architectural Painting Specification Manual requirements. Refer to MPI Manual in regard to specific requirements and as follows:
    - .1 Remove dust, dirt, and other surface debris by vacuuming, wiping with dry, clean cloths or compressed air.
    - .2 Wash surfaces with a biodegradable detergent and bleach where applicable and clean warm water using a stiff bristle brush to remove dirt, oil and other surface contaminants.
    - .3 Rinse scrubbed surfaces with clean water until foreign matter is flushed from surface.
    - .4 Allow surfaces to drain completely and allow to dry thoroughly.
    - .5 Prepare surfaces for water-based painting, water-based cleaners should be used in place of organic solvents.
    - .6 Use trigger operated spray nozzles for water hoses.
    - .7 Many water-based paints cannot be removed with water once dried. Minimize use of mineral spirits or organic solvents to clean up water-based paints.
  - .4 Clean following surfaces with high pressure water washing.
  - .5 Prevent contamination of cleaned surfaces by salts, acids, alkalis, other corrosive chemicals, grease, oil and solvents before prime coat is applied and between applications of remaining coats. Apply primer, paint, or pretreatment as soon as possible after cleaning and before deterioration occurs.
  - .6 Where possible, prime non-exposed surfaces of new wood surfaces before installation. Use

---

same primers as specified for exposed surfaces.

- .1 Apply vinyl sealer to MPI #36 over knots, pitch, sap and resinous areas.
- .2 Apply wood filler to nail holes and cracks.
- .3 Tint filler to match stains for stained woodwork.
- .7 Sand and dust between coats as required to provide adequate adhesion for next coat and to remove defects visible from a distance up to 1000 mm.
- .8 Clean metal surfaces to be painted by removing rust, loose mill scale, welding slag, dirt, oil, grease and other foreign substances in accordance with MPI requirements. Remove traces of blast products from surfaces, pockets and corners to be painted by brushing with clean brushes blowing with clean dry compressed air or vacuum cleaning.
- .9 Touch up of shop primers with primer as specified.
- .10 Do not apply paint until prepared surfaces have been accepted by Departmental Representative.

### 3.5 APPLICATION

- .1 Method of application to be as approved by Departmental Representative. Apply paint by brush roller air sprayer airless sprayer. Conform to manufacturer's application instructions unless specified otherwise.
- .2 Brush and Roller Application:
  - .1 Apply paint in uniform layer using brush and/or roller type suitable for application.
  - .2 Work paint into cracks, crevices and corners.
  - .3 Paint surfaces and corners not accessible to brush using spray, daubers and/or sheepskins. Paint surfaces and corners not accessible to roller using brush, daubers or sheepskins.
  - .4 Brush and/or roll out runs and sags, and over-lap marks. Rolled surfaces free of roller tracking and heavy stipple.

2013-07-06

- 
- .5 Remove runs, sags and brush marks from finished work and repaint.
  - .3 Spray application:
    - .1 Provide and maintain equipment that is suitable for intended purpose, capable of atomizing paint to be applied, and equipped with suitable pressure regulators and gauges.
    - .2 Keep paint ingredients properly mixed in containers during paint application either by continuous mechanical agitation or by intermittent agitation as frequently as necessary.
    - .3 Apply paint in uniform layer, with overlapping at edges of spray pattern. Back roll first coat application.
    - .4 Brush out immediately all runs and sags.
    - .5 Use brushes and rollers to work paint into cracks, crevices and places which are not adequately painted by spray.
  - .4 Use dipping, sheepskins or daubers only when no other method is practical in places of difficult access.
  - .5 Apply coats of paint continuous film of uniform thickness. Repaint thin spots or bare areas before next coat of paint is applied.
  - .6 Allow surfaces to dry and properly cure after cleaning and between subsequent coats for minimum time period as recommended by manufacturer.
  - .7 Sand and dust between coats to remove visible defects.
  - .8 Finish surfaces both above and below sight lines.
  - .9 Finish top, bottom, edges and cutouts of doors after fitting as specified for door surfaces.
- 
- |   |  |
|---|--|
| <u>3.6 MECHANICAL/<br/>ELECTRICAL<br/>EQUIPMENT</u> | <ul style="list-style-type: none"><li>.1 Paint finished area exposed conduits, piping, hangers, ductwork and other mechanical and electrical equipment with colour and finish to match adjacent surfaces, except as indicated.</li><li>.2 Paint exposed conduits, piping, hangers,</li></ul> |
|---|--|

ductwork and other mechanical and electrical equipment.

- .3 Other unfinished areas: leave exposed conduits, piping, hangers, ductwork and other mechanical and electrical equipment in original finish and touch up scratches and marks.
- .4 Touch up scratches and marks on factory painted finishes and equipment with paint as supplied by manufacturer of equipment.
- .5 Do not paint over nameplates.
- .6 Keep sprinkler heads free of paint.
- .7 Paint inside of ductwork where visible behind grilles, registers and diffusers with primer and one coat of matt black paint.
- .8 Paint fire protection piping red .
- .9 Paint disconnect switches for fire alarm system and exit light systems in red enamel.
- .10 Paint both sides and edges of backboards for telephone and electrical equipment before installation. Leave equipment in original finish except for touch-up as required, and paint conduits, mounting accessories and other unfinished items.
- .11 Do not paint interior transformers and substation equipment.

### 3.7 SITE TOLERANCES

- .1 Walls: no defects visible from a distance of 1000 mm at 90 degrees to surface.
- .2 Ceilings: no defects visible from floor at 45 degrees to surface when viewed using final lighting source.
- .3 Final coat to exhibit uniformity of colour and uniformity of sheen across full surface area.

### 3.8 FIELD QUALITY CONTROL

- .1 Interior painting and decorating work shall be inspected by Departmental Representative. Painting contractor shall notify Departmental Representative a minimum of one week prior to commencement of work and provide a copy of

project painting specification, plans and elevation drawings (including pertinent details) as well as a Finish Schedule.

- .2 Interior surfaces requiring painting shall be inspected by Departmental Representative who shall notify General Contractor in writing of defects or problems, prior to commencing painting work, or after prime coat shows defects in substrate.
- .3 Where "special" painting, coating or decorating system applications (i.e. elastomeric coatings) or non-MPI listed products or systems are to be used, paint or coating manufacturer shall provide as part of this work, certification of surfaces and conditions for specific paint or coating system application as well as on site supervision, inspection and approval of their paint or coating system application as required at no additional cost to Departmental Representative.
- .4 Standard of Acceptance:
  - .1 Walls: no defects visible from a distance of 1000 mm at 90 degrees to surface.
  - .2 Ceilings: no defects visible from floor at 45 degrees to surface when viewed using final lighting source.
  - .3 Final coat to exhibit uniformity of colour and uniformity of sheen across full surface area.
- .5 Advise Departmental Representative when surfaces and applied coating is ready for inspection. Do not proceed with subsequent coats until previous coat has been approved.
- .6 Retain purchase orders, invoices and other documents to prove conformance with noted MPI requirements when requested by Departmental Representative.

### 3.9 RESTORATION

- .1 Clean and re-install hardware items removed before undertaken painting operations.
- .2 Remove protective coverings and warning signs as soon as practical after operations cease.
- .3 Remove paint splashings on exposed surfaces that were not painted. Remove smears and

spatter immediately as operations progress,  
using compatible solvent.

- .4 Protect freshly completed surfaces from paint droppings and dust to approval of Departmental Representative. Avoid scuffing newly applied paint.
- .5 Restore areas used for storage, cleaning, mixing and handling of paint to clean condition as approved by Departmental Representative.