

PART 1 - GENERAL

1.1 RELATED SECTIONS

- .1 Section 01 74 21 - Construction/Demolition Waste Management and Disposal.
- .2 Section 31 05 17 - Aggregate Materials.
- .3 Section 32 11 16 - Granular Sub-base.

1.2 REFERENCES

- .1 American Society for Testing and Materials (ASTM)
 - .1 ASTM C117-95, Standard Test Methods for Material Finer Than 0.075 mm Sieve in Mineral Aggregates by Washing.
 - .2 ASTM C131-96, Standard Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine.
 - .3 ASTM C136-96a, Standard Test Method for Sieve Analysis of Fine and Coarse Aggregates.
 - .4 ASTM D698-00a, Standard Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400ft-lbf/ft³) (600kN-m/m³).
 - .5 ASTM D1557-00, Test Method for Laboratory Compaction Characteristics of Soil Using Modified Effort (56,000ft-lbf/ft³) (2,700kN-m/m³).
 - .6 ASTM D1883-99, Standard Test Method for CBR (California Bearing Ratio) of Laboratory Compacted Soils.
 - .7 ASTM D4318-00, Standard Test Methods for Liquid Limit, Plastic Limit and Plasticity Index of Soils.
- .2 Canadian General Standards Board (CGSB)
 - .1 CAN/CGSB-8.1-88, Sieves, Testing, Woven Wire, Inch Series.
 - .2 CAN/CGSB-8.2-M88, Sieves, Testing, Woven Wire, Metric.

1.3 DELIVERY, STORAGE, AND HANDLING

- .1 Deliver and stockpile aggregates in accordance with Section 31 05 17 - Aggregate Materials. Stockpile minimum 50% of total aggregate required prior to beginning operation.
- .2 Store cement in weathertight bins or silos that provide protection from dampness and easy access for inspection and identification of each shipment.

**PART 1 - GENERAL
(CONT'D)**

1.4 WASTE MANAGEMENT AND DISPOSAL

- .1 Separate and recycle waste materials in accordance with Section 01 74 21 - Construction/Demolition Waste Management And Disposal.
- .2 Divert unused granular material from landfill to local facility as approved by Departmental Representative.

1.5 MEASUREMENT FOR PAYMENT

- .1 Measure granular base in cubic meters place measure (CMPM) of compacted material incorporated into Work within the areas and to the thicknesses indicated on the drawings unless otherwise specified.
- .2 Measure maintenance Grade 3 in cubic metres place measure (CMPM) of compacted material into Work within the areas and to the thicknesses indicated on the drawings unless otherwise specified.

PART 2 - PRODUCTS

2.1 MATERIALS

- .1 Granular base: material in accordance with Section 31 05 17 - Aggregate Materials and following requirements:
 - .1 Crushed stone or gravel.
 - .2 Gradations to be within limits specified when tested to ASTM C136 and ASTM C117. Sieve sizes to CAN/CGSB-8.1 and CAN/CGSB-8.2.
 - .1 Gradation Method to:

Sieve Designation	% Passing
19 mm	100
9.5 mm	55-100
4.75 mm	35-60
1.20 mm	17-35
0.300 mm	7-20
0.075 mm	3-8

- .2 Liquid limit: to ASTM D4318, maximum 25.
- .3 Plasticity index: to ASTM D4318, maximum 6.
- .4 Los Angeles degradation: to ASTM C131. Max. % loss by weight: 45.

PART 2 - PRODUCTS (CONT'D)

2.1 MATERIALS (CONT'D)

- .1 (cont'd)
- .2 (cont'd)
- .5 Crushed particles: at least 60% of particles by mass within each of following sieve designation ranges to have at least 1 freshly fractured face. Material to be divided into ranges using methods of ASTM C136.

Passing	to	Retained on
19.0 mm		4.75 mm

- .2 Maintenance Grade 3: shall be composed of clean, hard, uncoated particles free from organic matter, clay lumps, and deleterious materials such as shale, slate, ochre, and schists.

Materials from deposits acceptable as to the quality of the particles, but deficient in size to provide the required gradation, may be accepted if the Contractor furnishes and satisfactorily incorporates into the product supplementary sizes from other sources to produce the required grading.

The Maintenance Grade 3 material shall be processed by crushing and, when necessary to eliminate surplus fines passing the 4.75 mm sieve, shall be screened and washed.

- .1 Gradation to be within the following limits:

Sieve Designation	% Passing
25.4 mm	100
9.51 mm	55-80
4.75 mm	35-60
1.20 mm	15-35
0.300 mm	5-20
0.075 mm	6-10

PART 3 - EXECUTION

3.1 SEQUENCE OF OPERATION

- .1 Place granular base after sub-base surface is inspected and approved by Departmental Representative.

PART 3 - EXECUTION
(CONT'D)

3.1 SEQUENCE OF OPERATION
(CONT'D)

- .2 Placing
 - .1 Construct granular base to depth and grade in areas indicated.
 - .2 Ensure no frozen material is placed.
 - .3 Place material only on clean unfrozen surface, free from snow and ice.
 - .4 Remove and replace that portion of layer in which material becomes segregated during spreading.
- .3 Compaction Equipment
 - .1 Compaction equipment to be capable of obtaining required material densities.
- .4 Compacting
 - .1 Compact to density not less than 100% corrected maximum dry density.
 - .2 Shape and roll alternately to obtain smooth, even and uniformly compacted base.
 - .3 Apply water as necessary during compacting to obtain specified density.
 - .4 In areas not accessible to rolling equipment, compact to specified density with mechanical tampers approved by Departmental Representative.
 - .5 Correct surface irregularities by loosening and adding or removing material until surface is within specified tolerance.

3.2 SITE TOLERANCES

- .1 Finished base surface to be within plus or minus 10 mm of established grade and cross section but not uniformly high or low.

3.3 PROTECTION

- .1 Maintain finished base in condition conforming to this Section until succeeding material is applied or until acceptance by Departmental Representative.