

PART 1 - GENERAL

- 1.1 REFERENCES
- .1 Health Canada/Workplace Hazardous Materials Information System (WHMIS)
 - .1 Material Safety Data Sheets (MSDS).
 - .2 The Master Painters Institute (MPI)
 - .1 Architectural Painting Specification Manual - current edition.
- 1.2 ACTION AND INFORMATIONAL SUBMITTALS
- .1 Submit in accordance with Section 01 33 00 - Submittal Procedures.
 - .2 Product Data:
 - .1 Submit manufacturer's instructions, printed product literature and data sheets for paint and coating products and include product characteristics, performance criteria, physical size, finish and limitations.
 - .2 Submit 2 copies of WHMIS MSDS in accordance with Section 01 35 29.00 - Health and Safety Requirements.
 - .3 Samples:
 - .1 Submit 200 x 300 mm sample panels of each paint with specified paint or coating in colours, gloss/sheen and textures required to MPI Painting Specification Manual standards.
 - .4 Certificates: submit product certificates signed by manufacturer certifying materials comply with specified performance characteristics and criteria and physical requirements.
- 1.3 DELIVERY, STORAGE AND HANDLING
- .1 Deliver, store and handle materials in accordance with Section 01 61 00 - Common Product Requirements and with manufacturer's written instructions.
 - .2 Delivery and Acceptance Requirements: deliver materials to site in original factory packaging, labelled with manufacturer's name and address.
 - .3 Storage and Handling Requirements:
 - .1 Provide and maintain dry, temperature controlled, secure storage.
 - .2 Store painting materials and supplies away from heat generating devices.
 - .3 Store materials and equipment in well ventilated area within temperature as recommended by manufacturer.
 - .4 Fire Safety Requirements:
 - .1 Supply 9 kg Type ABC fire extinguisher adjacent to storage area.
 - .2 Store oily rags, waste products, empty containers and materials subject to spontaneous combustion in ULC approved, sealed containers and remove from site on a daily basis.
 - .3 Handle, store, use and dispose of flammable and combustible materials in accordance with National Fire Code of Canada requirements.
- 1.4 SITE CONDITIONS
- .1 Heating, Ventilation and Lighting:
 - .1 Ventilate enclosed spaces in accordance with Section 01 51 00 -

- .2 Temporary Utilities.
- .2 Co-ordinate use of existing ventilation system with Departmental Representative and ensure its operation during and after application of paint as required.
- .3 Provide minimum lighting level of 323 Lux on surfaces to be painted.
- .2 Temperature, Humidity and Substrate Moisture Content Levels:
 - .1 Apply paint finishes when ambient air and substrate temperatures at location of installation can be satisfactorily maintained during application and drying process, within MPI and paint manufacturer's prescribed limits.
 - .2 Test concrete, masonry and plaster surfaces for alkalinity as required.
 - .3 Apply paint to adequately prepared surfaces, when moisture content is below paint manufacturer's prescribed limits.
- .3 Additional application requirements:
 - .1 Apply paint finish in areas where dust is no longer being generated by related construction operations or when wind or ventilation conditions are such that airborne particles will not affect quality of finished surface.
 - .2 Apply paint in occupied facilities during silent hours only. Schedule operations to approval of Departmental Representative such that painted surfaces will have dried and cured sufficiently before occupants are affected.

PART 2 - PRODUCTS

2.1 MATERIALS

- .1 Supply paint materials for paint systems from single manufacturer.
- .2 Conform to latest MPI requirements for painting work including preparation and priming.
- .3 Materials in accordance with MPI - Architectural Painting Specification Manual "Approved Product" listing.

PART 3 - EXECUTION

3.1 GENERAL

- .1 Compliance: comply with manufacturer's written recommendations or specifications, including product technical bulletins, handling, storage and installation instructions, and data sheets.
- .2 Perform preparation and operations for interior painting in accordance with MPI - Architectural Painting Specifications Manual except where specified otherwise.

3.2 EXAMINATION

- .1 Investigate existing substrates for problems related to proper and complete preparation of surfaces to be painted. Report to Departmental Representative damages, defects, unsatisfactory or unfavourable conditions before proceeding with work.
- .2 Conduct moisture testing of surfaces to be painted using properly calibrated

electronic moisture meter, except test concrete floors for moisture using simple "cover patch test". Do not proceed with work until conditions fall within acceptable range as recommended by manufacturer.

3.3 PREPARATION

- .1 Protection of in-place conditions:
 - .1 Protect existing building surfaces and adjacent structures from paint splatters, markings and other damage by suitable non-staining covers or masking. If damaged, clean and restore surfaces as directed by Departmental Representative.
- .2 Surface Preparation:
 - .1 Place "WET PAINT" signs in occupied areas as painting operations progress. Signs to approval of Departmental Representative.
 - .2 Clean and prepare surfaces in accordance with MPI - Architectural Painting Specification Manual specific requirements and coating manufacturer's recommendations.
 - .3 Prevent contamination of cleaned surfaces by salts, acids, alkalis, other corrosive chemicals, grease, oil and solvents before prime coat is applied and between applications of remaining coats. Apply primer, paint, or pretreatment as soon as possible after cleaning and before deterioration occurs.
 - .4 Sand and dust between coats as required to provide adequate adhesion for next coat and to remove defects visible from a distance up to 1000 mm.
 - .5 Touch up of shop primers with primer as specified.

3.4 APPLICATION

- .1 Paint only after prepared surfaces have been accepted by Departmental Representative.
- .2 Use method of application approved by Departmental Representative.
 - .1 Conform to manufacturer's application recommendations.
- .3 Apply coats of paint in continuous film of uniform thickness.
 - .1 Repaint thin spots or bare areas before next coat of paint is applied.
- .4 Allow surfaces to dry and properly cure after cleaning and between subsequent coats for minimum time period as recommended by manufacturer.
- .5 Sand and dust between coats to remove visible defects.

3.5 CLEANING

- .1 Progress Cleaning: clean in accordance with Section 01 74 11 - Cleaning.
 - .1 Leave Work area clean at end of each day.
- .2 Final Cleaning: upon completion remove surplus materials, rubbish, tools and equipment in accordance with Section 01 74 11 - Cleaning.
- .3 Place paint and primer defined as hazardous or toxic waste, including tubes and containers, in containers or areas designated for hazardous waste.

END OF SECTION