

PART 1 - GENERAL

1.1 SECTION INCLUDES

- .1 Materials and application of asphalt tack coat to an existing asphalt or concrete surface prior to asphalt paving.

1.2 RELATED SECTIONS

- .1 Section 01 33 00 - Submittal Procedures.

1.3 REFERENCES

- .1 American Society for Testing and Materials International, (ASTM)
- .2 ASTM D140/D140M-09 , Standard Practice for Sampling Bituminous Materials.
- .3 Canadian General Standards Board (CGSB)
 - .1 CAN/CGSB-16.2-M89, Emulsified Asphalts, Anionic Type, for Road Purposes.

1.4 SUBMITTALS

- .1 Submit samples in accordance with Section 01 33 00 - Submittal Procedures.

1.5 QUALITY ASSURANCE

- .1 Upon request by Departmental Representative, submit manufacturer's test data and certification that asphalt tack coat material meets requirements of this section.

1.6 DELIVERY, STORAGE AND HANDLING

- .1 Deliver, store and handle materials in accordance with. ASTM D140-01.
- .2 Provide, maintain and restore asphalt storage area.

PART 2 - PRODUCTS

2.1 MATERIALS

- .1 Anionic emulsified asphalt: to CAN/CGSB-16.2, grade: SS-1.
- .2 Water: clean, potable, free from foreign matter.

2.2 EQUIPMENT

- .1 Pressure distributor to be:
 - .1 Designed, equipped, maintained and operated so that asphalt material can be:
 - .1 Maintained at even temperature.
 - .2 Applied uniformly on variable widths of surface up to 5 m.
 - .3 Applied at readily determined and controlled rates from 0.2 to 5.4 L/m² with uniform pressure, and with an allowable variation from any specified rate not exceeding 0.1 L/m².
 - .4 Distributed in uniform spray without atomization at temperature required.
 - .2 Equipped with meter, registering metres of travel per minute, visibly located to enable truck driver to maintain constant speed required for application at specified rate.
 - .3 Equipped with pump having flow meter graduated in units of 5 L or less per minute passing through nozzles and readily visible to operator. Pump power unit to be independent of truck power unit.
 - .4 Equipped with an easily read, accurate and sensitive device which registers temperature of liquid in reservoir.
 - .5 Equipped with accurate volume measuring device or calibrated tank.
 - .6 Equipped with nozzles of same make and dimensions, adjustable for fan width and orientation.
 - .7 Equipped with nozzle spray bar, with operational height adjustment.
 - .8 Cleaned if previously used with incompatible asphalt material.

PART 3 - EXECUTION

3.1 APPLICATION

- .1 Obtain Departmental Representative's approval of surface before applying asphalt tack coat.
 - .2 Apply asphalt tack coat only on clean and dry surface.
 - .3 Dilute asphalt emulsion with water at 1:1 ratio for application.
 - .1 Mix thoroughly by pumping or other method approved by Departmental Representative.
 - .4 Apply asphalt tack coat evenly to pavement surface at rate as directed by Departmental Representative but not to exceed 0.7 L/m².
 - .5 Paint contact surfaces of curbs, gutters, headers, manholes and like structures with thin, uniform coat of asphalt tack coat material.
-

- .6 Do not apply asphalt tack coat when air temperature is less than 10 degrees C or when rain is forecast within 2 hours of application.
- .7 Apply asphalt tack coat only on unfrozen surface.
- .8 Evenly distribute localized excessive deposits of tack coat by brooming as directed by Departmental Representative.
- .9 Where traffic is to be maintained, treat no more than one half of width of surface in one application.
- .10 Keep traffic off tacked areas until asphalt tack coat has set.
- .11 Re-tack contaminated or disturbed areas as directed by Departmental Representative.
- .12 Permit asphalt tack coat to set before placing asphalt pavement.