

PART 1- GENERAL

- 1.1 RELATED WORK .1 General Requirements Division 1
- 1.2 SUMMARY .1 This Section specifies caulking and sealants not specified in other Sections.
.2 Refer to other sections for other caulking and sealants.
- 1.3 REFERENCES .1 CAN/CGSB-19.13-M87 Sealing Compound, One-component, Elastomeric, Chemical Curing.
- 1.4 SAMPLES .1 Submit samples in accordance with Section 01 33 00 Submittal Procedures.
.2 Submit duplicate samples of each type of material and colour.
- 1.5 DELIVERY, STORAGE, AND HANDLING
- .1 Deliver, handle, store and protect materials in accordance with Section 01 61 00 - Common Product Requirements.
.2 Deliver and store materials in original wrappings and containers with manufacturer's seals and labels, intact. Protect from freezing, moisture, water and contact with ground or floor.
- 1.6 ENVIRONMENTAL REQUIREMENTS
- .1 Comply with requirements of Workplace Safety Hazardous Materials Information System (WHMIS) regarding use, handling, storage, and disposal of hazardous materials; and regarding labeling and provision of material safety data sheets acceptable to Labour Canada.
.2 Conform to manufacturer's recommended temperatures, relative humidity, and substrate moisture content for application and curing of sealants including special conditions governing use.
.3 Ventilate area of work as directed by Department Representative by use of approved portable supply and exhaust fans.
- 1.7 QUALITY ASSURANCE .1 Provide Certificate of Quality Compliance of the selection and application of sealant. Provide list of sealants used on the project and where applied.

PART 2 - PRODUCTS

2.1 SEALANT MATERIALS

- .1 Sealants and Caulking compounds must:
 - .1 Meet or exceed all applicable governmental and industrial safety and performance standards; and
 - .2 Be manufactured and transported in such a manner that all steps of the process, including the disposal of waste products arising there from, will meet the requirements of all applicable governmental acts, by laws and regulations including, for facilities located in Canada, the Fisheries Act and the Canadian Environmental Protection Act (CEPA).
- .2 Sealant and caulking compounds must not be formulated or manufactured with: aromatic solvents, fibrous talc or asbestos, formaldehyde, halogenated solvents, mercury, lead, cadmium, hexavalent chromium, barium or their compounds, except barium sulfate.
- .3 Sealant and caulking compounds must not contain a total of volatile organic compound (VOC's) in excess of 5% by height as calculated from records of the amounts of constituents used to make the product.
- .4 Sealant and caulking compounds must be accompanied by detailed instructions for proper application so as to minimize health concerns and maximize performance, and information describing proper disposal methods.
- .5 Caulking that emits strong odours, contains toxic chemicals or is not certified as mould resistant shall not be used in air handling units.
- .6 When low toxicity caulks are not possible, confine usage to areas which off-gas to the exterior, are contained behind air barriers, or are applied several months before occupancy to maximize off-gas time.
- .7 Sealants acceptable for use on this project must be listed on CGSB Qualified Products List issued by CGSB Qualification Board for Joint Sealants. Where sealants are qualified with primers use only these primers.

2.2 SEALANT MATERIAL DESIGNATIONS

- .1 Urethanes One Part.
 - .1 Non-Sag to CAN/CGSB-19.13, Type 2.
- .2 Preformed Compressible and Non-Compressible back-up materials.

JOINT SEALANTS

- .1 Polyethylene, Urethane, Neoprene or Vinyl Foam.
 - .1 Extruded open closed cell foam backer rod.
 - .2 Size: oversize 30 to 50%.
- .2 Neoprene or Butyl Rubber.
 - .1 Round solid rod, Shore A hardness 70.
- .3 High Density Foam.
 - .1 Extruded closed cell polyvinyl chloride (PVC), extruded polyethylene, closed cell, Shore A hardness 20, tensile strength 140 to 200 kPa, extruded polyolefin foam, 32 kg/m3 density, or neoprene foam backer, size as recommended by manufacturer.
- .4 Bond Breaker Tape.
 - .1 Polyethylene bond breaker tape which will not bond to sealant.

2.3 SEALANT SELECTION .1 Perimeters of exterior openings where frames meet exterior facade of building, Sealant Type CAN/CGSB- 19.13-M87.

2.4 JOINT CLEANER .1 Non-corrosive and non-staining type, compatible with joint forming materials and sealant recommended by sealant manufacturer.
.2 Primer: as recommended by manufacturer.

PART 3 - EXECUTION

3.1 PROTECTION .1 Protect installed work of other trades from staining or contamination.

3.2 PREPARATION OF JOINT SURFACES

- .1 Examine joint sizes and conditions to establish correct depth to width relationship for installation of backup materials and sealants.
- .2 Clean bonding joint surfaces of harmful matter substances including dust, rust, oil grease, and other matter which may impair work.
- .3 Do not apply sealants to joint surfaces treated with sealer, curing compound, water repellent, or other coatings unless tests have been performed to ensure compatibility of materials. Remove coatings as required.
- .4 Ensure joint surfaces are dry and frost free.
- .5 Prepare surfaces in accordance with manufacturer's directions.

JOINT SEALANTS

- 3.3 PRIMING .1 Where necessary to prevent staining, mask adjacent surfaces prior to priming and caulking.
- .2 Prime sides of joints in accordance with sealant manufacturer's instructions immediately prior to caulking.
- 3.4 BACKUP MATERIAL .1 Apply bond breaker tape where required to manufacturer's instructions.
- .2 Install joint filler to achieve correct joint depth and shape, with approximately 30% compression.
- 3.5 MIXING .1 Mix materials in strict accordance with sealant manufacturer's instructions.
- 3.6 APPLICATION .1 Sealant.
- .1 Apply sealant in accordance with manufacturer's written instructions.
- .2 Mask edges of joint where irregular surface or sensitive joint border exists to provide neat joint.
- .3 Apply sealant in continuous beads.
- .4 Apply sealant using gun with proper size nozzle.
- .5 Use sufficient pressure to fill voids and joints solid.
- .6 Form surface of sealant with full bead, smooth, free from ridges, wrinkles, sags, air pockets, embedded impurities.
- .7 Tool exposed surfaces before skinning begins to give slightly concave shape.
- .8 Remove excess compound promptly as work progresses and upon completion.
- .2 Curing.
- .1 Cure sealants in accordance with sealant manufacturer's instructions.
- .2 Do not cover up sealants until proper curing has taken place.
- .3 Cleanup.
- .1 Clean adjacent surfaces immediately and leave work neat and clean.
- .2 Remove excess and droppings, using recommended cleaners as work progresses.
- .3 Remove masking tape after initial set of sealant.

END OF SECTION