

PART 1 - GENERAL

- | | | |
|--|----|--|
| 1.1 <u>RELATED SECTIONS</u> | .1 | Section 013300 – Submittal Procedures |
| | .2 | Section 017411 – Cleaning |
| 1.2 <u>MEASUREMENT FOR PAYMENT</u> | .1 | Item No. C-011 Removal / Obliteration of Existing Pavement Markings - The work includes the removal of existing pavement markings, as indicated on the Contract Drawings. Measurement for payment shall be by metre of 10cm wide solid painted lines (either yellow or white) obliterated / removed. The unit price bid will be full compensation for all materials, labour, equipment necessary to do the work. |
| | .2 | No measurement for payment will be made under this section for cleaning pavement surfaces. Pavement cleaning performed under this section will be incidental to work in other related sections. |
| 1.3 <u>ACTION AND INFORMATIONAL SUBMITTALS</u> | .1 | Submit in accordance with Section 013300 - Submittal Procedures. |
| | .2 | Product Data: |
| | .1 | Submit manufacturer's instructions, printed product literature and data sheets for each type of abrasives and solvent used on project. |
| | .2 | Submit 2 copies of WHMIS MSDS in accordance with Section 013529.06 - Health and Safety Requirements and 013543 - Environmental Procedures. |

PART 2 - PRODUCTS

- | | | |
|----------------------|----|--|
| 2.1 <u>MATERIALS</u> | .1 | Abrasives and solvents used for removal of paint, oil, grease, rubber deposits: proprietary products specially designed for pavement cleaning, subject to approval by Departmental Representative. |
|----------------------|----|--|

PART 3 - EXECUTION

- | | | |
|---------------------------------------|----|--|
| 3.1 <u>REMOVING PAVEMENT MARKINGS</u> | .1 | Remove rubber tire deposits and paint markings, in areas as directed by Departmental Representative, by sand/water blasting, rotary grinding, heater planing or other method approved in writing by Departmental Representative. |
| | .2 | Exercise care to avoid dislodging of coarse aggregate particles, excessive removal of fines, damage to bituminous binder or damage to joint and crack sealers. |
| | .3 | Do not heat pavement surfaces above 12 degrees C, when using heater planing equipment.. |

3.2 PAVEMENT SURFACE CLEANING

- .1 Remove sealing compound which has protruded excessively, where directed by Departmental Representative.
 - .1 Dispose of removed material as directed by Departmental Representative.
- .2 Remove dust, contaminants, loose and foreign materials, oil and grease, in areas as directed by and by method approved in writing by Departmental Representative.
- .3 Use rotary power brooms and / or vacuum sweepers supplemented by hand brooming.

3.3 CLEANING

- .1 Progress Cleaning: clean in accordance with Section 017411 - Cleaning.
 - .1 Leave Work area clean at end of each day.
- .2 Final Cleaning: upon completion remove surplus materials, rubbish, tools and equipment in accordance with Section 017411 - Cleaning.

***** END OF SECTION *****