

**PART 1 - GENERAL**

1.1 RELATED SECTIONS

No Object.

1.2 REFERENCES

- .1 Canadian General Standards Board (CGSB)
  - .1 CAN/CGSB-1.5-99, Low Flash Petroleum Spirits Thinner.
  - .2 CAN/CGSB 1.74-01, Alkyde Traffic Paint.
- .2 Green Seal Environmental Standards (GS)
  - .1 GS-11-2008, 2nd Edition, Paints and Coatings.
- .3 Health Canada / Workplace Hazardous Materials Information System (WHMIS)
  - .1 Material Safety Data Sheets (MSDS).
- .4 The Master Painters Institute (MPI)
  - .1 Architectural Painting Specification Manual - current edition.
- .5 South Coast Air Quality Management District (SCAQMD), California State, Regulation XI. Source Specific Standards
  - .1 SCAQMD Rule 1113-A2007, Architectural Coatings.

1.3 ACTION AND INFORMATIONAL SUBMITTALS

- .1 Submit in accordance with Section 013300 - Submittal Procedures.
- .2 Product Data:
  - .1 Submit manufacturer's printed product literature and data sheets for pavement markings and include product characteristics, performance criteria, physical size, finish and limitations.
  - .2 Submit two copies of WHMIS MSDS in accordance with Section 013529.06 - Health and Safety Requirements.
- .3 Samples:
  - .1 Submit to Departmental Representative following material sample quantities at least 4 weeks prior to commencing work.
    - .1 Two 1 L samples of each type of paint.

1.4 DELIVERY, STORAGE AND HANDLING

- .1 Delivery and Acceptance Requirements: deliver materials to site in original factory packaging, labelled with manufacturer's name and address.
- .2 Storage and Handling Requirements:
  - .1 Store materials off ground and in accordance with manufacturer's recommendations in clean, dry, well-ventilated area.
  - .2 Replace defective or damaged materials with new.

1.5 BASIS OF PAYMENT

- .1 Pavement markings - The lump sum price bid will be full compensation for all materials, labour, equipment required to layout and install the required pavement markings as indicated on the Contract Drawings.

- .2 Crosswalks, stop bars and cross-hatching shall be included in the lump sum price bid.

**PART 2 - PRODUCTS**

2.1 MATERIALS

- .1 Paint:
  - .1 To MPI -EXT 2.1B, Alkyd zone/traffic marking.
  - .2 Paints: in accordance with MPI recommendation for surface conditions.
    - .1 Paints: maximum VOC limit 100 g/L to SCAQMD Rule 1113 to GS-11.
  - .3 Colour: to MPI listed, yellow and white.
  - .4 Upon request, Departmental Representative will supply qualified product list of paints applicable to work. Qualified paints may be used but Departmental Representative reserves right to perform further tests.
- .2 Thinner: to MPI listed manufacturer.

**PART 3 - EXECUTION**

3.1 EXAMINATION

- .1 Verification of Conditions: verify conditions of substrates and surfaces to receive pavement markings previously installed under other Sections or Contracts are acceptable for product installation in accordance with MPI instructions prior to pavement markings installation.
  - .1 Visually inspect substrate in presence of Departmental Representative.
- .2 Pavement surface: dry, free from water, frost, ice, dust, oil, grease and other deleterious materials.
- .3 Proceed with Work only after unacceptable conditions have been rectified.

3.2 EQUIPMENT REQUIREMENTS

- .1 Paint applicator: approved pressure type with positive shut-off distributor capable of applying paint in single, double and dashed lines and capable of applying marking components uniformly, at rates specified, and to dimensions as indicated.

3.3 APPLICATION

- .1 Pavement markings: laid out by Contractor and verified by Departmental Representative.
- .2 Unless otherwise approved by Departmental Representative, apply paint only when air temperature is above 10 degrees C, wind speed is less than 60 km/h and no rain is forecast within next 4 hours.
- .3 Apply traffic paint evenly at rate of 3 m<sup>2</sup> /L.
- .4 Do not thin paint unless approved by Departmental Representative.
- .5 Symbols and letters to dimensions indicated.

- 
- |   |    |  |
|---|----|--|
|   | .6 | Paint lines: of uniform colour and density with sharp edges.   |
|   | .7 | Thoroughly clean distributor tank before refilling with paint of different colour.   |
| 3.4 <u>TOLERANCE</u>                    | .1 | Paint markings: within plus or minus 12 mm of dimensions indicated.  |
|   | .2 | Remove incorrect markings as directed by Departmental Representative.  |
| 3.5 <u>CLEANING</u>                     | .1 | Progress Cleaning: clean in accordance with Section 017411 - Cleaning.   |
|   | .1 | Leave Work area clean at end of each day.  |
|   | .2 | Final Cleaning: upon completion remove surplus materials, rubbish, tools and equipment in accordance with Section 017411 - Cleaning. |
| 3.6 <u>PROTECTION OF COMPLETED WORK</u> | .1 | Protect pavement markings until dry.   |
|   | .2 | Repair damage to adjacent materials caused by pavement marking application.  |

**\*\*\* END OF SECTION \*\*\***