

Approved: 2007-12-31

Part 1 General

1.1 REFERENCES

- .1 American Society for Testing and Materials International (ASTM)
 - .1 ASTM F1303-04, Standard Specification for Sheet Vinyl Floor Covering with Backing.
- .2 Canada Green Building Council (CaGBC)
 - .1 LEED Canada-NC Version 1.0-2004, LEED (Leadership in Energy and Environmental Design): Green Building Rating System Reference Package For New Construction and Major Renovations.
- .3 Health Canada/Workplace Hazardous Materials Information System (WHMIS)
 - .1 Material Safety Data Sheets (MSDS).
- .4 South Coast Air Quality Management District (SCAQMD), California State
 - .1 SCAQMD Rule 1113-04, Architectural Coatings.
 - .2 SCAQMD Rule 1168-05, Adhesives and Sealants Applications.

1.2 SUBMITTALS

- .1 Provide submittals in accordance with Section 01 33 00 - Submittal Procedures
- .2 Provide product data in accordance with Section 01 33 00 - Submittal Procedures.
- .3 Provide samples in accordance with Section 01 33 00 - Submittal Procedures.
 - .1 Submit duplicate 300 x 300 mm sample pieces of sheet material, 300 mm long base, edge strips.
- .4 Closeout Submittals:
 - .1 Provide maintenance data for resilient flooring for incorporation into manual specified in Section 01 78 00 - Closeout Submittals.

1.3 DELIVERY, STORAGE AND HANDLING

- .1 Deliver, store and handle materials in accordance with Section 01 61 00 - Common Product Requirements.

1.4 AMBIENT CONDITIONS

- .1 Maintain air temperature and structural base temperature at flooring installation area above 20 degrees for 48 hours before, during and 48 hours after installation.

1.5 MAINTENANCE

- .1 Extra Materials:

- .1 Provide extra materials of resilient sheet flooring and adhesives in accordance with Section 01 78 00 - Closeout Submittals.
- .2 Provide 6 m² of each colour, pattern and type flooring material required for project for maintenance use.
- .3 Extra materials one piece and from same production run as installed materials.
- .4 Identify each roll of sheet flooring and each container of adhesive.
- .5 Deliver to PWGSC Representative upon completion of the work of this section.
- .6 Store where directed by PWGSC Representative.

Part 2 Products

2.1 MATERIALS

- .1 Linoleum sheet flooring: composed of natural ingredients which are mixed and calendered onto a jute backing:
 - .1 Pattern: marbled.
 - .2 Thickness: 2.5 mm.
 - .3 Colour: selected by PWGSC Representative.
- .2 Resilient base: continuous, top set, complete with premoulded end stops and external corners:
 - .1 Type: rubber.
 - .2 Style: straight.
 - .3 Thickness: 3.17 mm.
 - .4 Height: 101.6 mm.
 - .5 Lengths: cut lengths minimum 2400 mm.
 - .6 Colour: selected by PWGSC Representative.
- .3 Primers and adhesives: of types recommended by resilient flooring manufacturer for specific material on applicable substrate, above, on or below grade.
- .4 Sub-floor filler and leveller: as recommended by flooring manufacturer for use with their product.
- .5 Metal edge strips:
 - .1 Aluminum extruded, smooth, mill finish stainless steel with lip to extend under floor finish, shoulder flush with top of adjacent floor finish.
- .6 Sealer and wax: type recommended by resilient flooring material manufacturer for material type and location.

Part 3 Execution

3.1 MANUFACTURER'S INSTRUCTIONS

- .1 Compliance: comply with manufacturer's written recommendations or specifications, including product technical bulletins, handling, storage and installation instructions, and datasheets.

3.2 SITE VERIFICATION OF CONDITIONS

- .1 Ensure concrete floors are clean and dry by using test methods recommended by flooring manufacturer.

3.3 PREPARATION

- .1 Remove existing resilient flooring.
- .2 Remove or treat old adhesives to prevent residual, old flooring adhesives from bleeding through to new flooring and/or interfering with the bonding of new adhesives.
- .3 Clean floor and apply filler; trowel and float to leave smooth, flat hard surface. Prohibit traffic until filler cured and dry.
- .4 Remove sub-floor ridges and bumps. Fill low spots, cracks, joints, holes and other defects with sub-floor filler.
- .5 Prime concrete slab to resilient flooring manufacturer's printed instructions.

3.4 APPLICATION: FLOORING

- .1 Provide high ventilation rate, with maximum outside air, during installation, and for 48 to 72 hours after installation. If possible, vent directly to outside. Do not let contaminated air recirculate through district or whole building air distribution system. Maintain extra ventilation for at least one month following building occupation.
- .2 Apply adhesive uniformly using recommended trowel. Do not spread more adhesive than can be covered by flooring before initial set takes place.
- .3 Lay flooring with seams parallel to building lines to produce a minimum number of seams. Border widths minimum 1/3 width of full material.
- .4 Run sheets in direction of traffic. Double cut sheet joints heat weld according to manufacturer's printed instructions.
- .5 Heat weld seams of linoleum sheet flooring in accordance with manufacturer's printed instructions.
- .6 As installation progresses, and after installation roll flooring with 45 kg minimum roller to ensure full adhesion.
- .7 Cut flooring around fixed objects.

- .8 Install feature strips and floor markings where indicated. Fit joints tightly.
- .9 Install flooring in pan type floor access covers. Maintain floor pattern.
- .10 Continue flooring over areas which will be under built-in furniture.
- .11 Continue flooring through areas to receive movable type partitions without interrupting floor pattern.
- .12 Terminate flooring at centreline of door in openings where adjacent floor finish or colour is dissimilar.
- .13 Install metal edge strips at unprotected or exposed edges where flooring terminates.

3.5 APPLICATION: BASE

- .1 Lay out base to keep number of joints at minimum.
- .2 Clean substrate and prime with one coat of adhesive.
- .3 Apply adhesive to back of base.
- .4 Set base against wall and floor surfaces tightly by using 3 kg hand roller.
- .5 Install straight and level to variation of 1:1000.
- .6 Scribe and fit to door frames and other obstructions. Use premoulded end pieces at flush door frames.
- .7 Cope internal corners. Use premoulded corner units for right angle external corners. Use formed straight base material for external corners of other angles.
- .8 Use toeless type base where floor finish will be carpet, coved type elsewhere.
- .9 Install toeless type base before installation of carpet on floors.
- .10 Heat weld base in accordance with manufacturer's printed instructions.

3.6 FIELD QUALITY CONTROL

- .1 Manufacturer's Field Services:
 - .1 Provide manufacturer's field services consisting of product use recommendations and periodic site visits for inspection of product installation in accordance with manufacturer's instructions.

3.7 CLEANING

- .1 Proceed in accordance with Section 01 74 11 - Cleaning.
- .2 Remove excess adhesive from floor, base and wall surfaces without damage.
- .3 Clean, seal and wax floor and base surface to flooring manufacturer's printed instructions.

3.8 PROTECTION

- .1 Protect new floors from time of final set of adhesive until final inspection.
- .2 Prohibit traffic on floor for 48 hours after installation.
- .3 Use only water-based coating for linoleum.

END OF SECTION