

**PART 1 GENERAL**

**1.1 Summary**

- .1 This Section defines correction to maximum dry density to take into account aggregate particles larger than 4.75 mm.

**1.2 References**

- .1 American Society for Testing and Materials (ASTM)
  - .1 ASTM C127-88, Standard Test Method for Specific Gravity and Absorption of Coarse Aggregate.
  - .2 ASTM D698, Standard Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400 ft-lbf/ft<sup>3</sup>) (600kN-m/m<sup>3</sup>).
  - .3 ASTM D1557, Test Method for Laboratory Compaction Characteristics of Soil Using Modified Effort (56,000 ft-lbf/ft<sup>3</sup>).
  - .4 ASTM D4253, Standard Test Methods for Maximum Index Density and Unit Weight of Soils Using a Vibratory Table.

**1.3 Definitions**

- .1 Corrected maximum dry density is defined as:
  - .1  $D = (D1 \times D2) / (F1 \times D2 + (F2 \times D1))$
  - .2 Where: D = corrected maximum dry density kg/m<sup>3</sup>.
    - .1 F1 = fraction (decimal) of total field sample passing 4.75 mm sieve.
    - .2 F2 = fraction (decimal) of total field sample retained on 4.75 mm sieve (equal to 1.00 - F1)
    - .3 D1 = maximum dry density, kg/m<sup>3</sup> of material passing 4.75 mm sieve determined in accordance with Method A C of ASTM D698.
    - .4 D2 = bulk density, kg/m<sup>3</sup>, of material retained on 4.75 mm sieve, equal to 1000G where G is bulk specific gravity (dry basis) of material when tested to ASTM C127.
  - .3 For free draining aggregates, determine D1 (maximum dry density) to ASTM D4253, dry method when directed by Departmental Representative.

**PART 2 PRODUCTS (NOT APPLICABLE)**

**PART 3 EXECUTION (NOT APPLICABLE)**

**END OF SECTION**