

Wharf Reconstruction
Lawn, NL
P/N: 718889

Page 1
2016-07-06

PART 1 - GENERAL

1.1 REFERENCES

- .1 American Wood-Preservers' Association (AWPA)
 - .1 AWPA M2-01, Standard Inspection of Treated Wood Products.
 - .2 AWPA M4-06, Standard for the Care of Preservative-Treated Wood Products.
- .2 Canadian Standards Association (CSA)
 - .1 CSA O80 Series-97 (R2007), Wood Preservation.
 - .2 CSA O80.201-97, Standard for Hydrocarbon Solvents for Preservatives. This Standard covers hydrocarbon solvents for preparing solutions of preservatives. This is not stand alone specification
 - .3 CSA O322-02, Procedure for Certification of Pressure-Treated Wood Materials for Use in Preserved Wood Foundations.

1.2 QUALITY ASSURANCE

- .1 Testing of products treated with preservative by pressure impregnation will be carried out by the manufacturer's testing laboratory to AWPA M2, and revisions specified in CSA O80 Series, Supplementary Requirements to AWPA M2.
- .2 Inspection and testing of timber materials will be carried out by the manufacturer.

1.3 CERTIFICATES AND ASSAY RETENTION RESULTS

- .1 Submit certificates and assay retention results in accordance with Section 01 33 00 - Submittal Procedures.
- .2 For products treated with preservative by pressure impregnation submit following information certified by authorized signing officer of treatment plant:
 - .1 Information listed in AWPA M2 and

Wharf Reconstruction
Lawn, NL
P/N: 718889

Page 2
2016-07-06

revisions specified in CSA O80 Series,
Supplementary Requirement to AWP M2
applicable to specified treatment.

.2 Moisture content after drying following
treatment with water-borne preservative.

.3 Assay retentions results representing
each treated batch of supplied timber.

.4 Acceptable types of paint, stain, and
clear finishes that may be used over treated
materials to be finished after treatment.

1.4 WASTE
MANAGEMENT AND
DISPOSAL

.1 Do not dispose of preservative treated wood
through incineration.

.2 Do not dispose of preservative treated wood
with other materials destined for recycling
or reuse.

.3 Dispose of treated wood, end pieces, wood
scraps and sawdust at sanitary landfill
approved by Departmental Representative.

.4 Dispose of unused wood preservative material
at official hazardous material collections
site approved by Departmental
Representative.

.5 Do not dispose of unused preservative
material into sewer system, into streams,
lakes, onto ground or in other location where
they will pose health or environmental
hazard.

PART 2 - PRODUCTS

2.1 MATERIALS

.1 Preservative: to CSA-O80 Series.

.2 Solvent: to CSA-O80.201.

2.2 PRESERVATIVE
TREATMENTS

.1 Treat to CSA 080, commodity standard 080.18,
Table 1 and its referenced standards, with

Wharf Reconstruction
Lawn, NL
P/N: 718889

Page 3
2016-07-06

the following minimum assay retentions:

Species	CCA kg/m3	ACA kg/m3
Dimension Timber		
-Coast Douglas Fir	24	24
-Western/Eastern Hemlock	24	24
-Hemlock, Douglas Fir (Wheelguard, Wheelguard Blocking)	10	10
-Birch or Maple	Treat to Refusal	

Note: Birch or maple must be air dried for six (6) months in weather protected environment or kiln dried.

PART 3 - EXECUTION

3.1 FIELD TREATMENT

- .1 Handle pressure treated material in a manner that will avoid damage which may expose untreated material. Rejection of any damaged material may result and replacement will be at the Contractor's expense.
- .2 Fill all bored bolt holes with preservative immediately after boring. Use a pressurized container with hose to apply preservative, or some alternate method acceptable to the Departmental Representative.
- .3 Fill all unused bored holes and spike holes with tight fitting treated wooden plugs.

3.2 CUTTING

- .1 Field cuts, if authorized, are to receive three (3) liberal coats of the applicable preservative applied to dry wood on each

Wharf Reconstruction
Lawn, NL
P/N: 718889

Page 4
2016-07-06

application.

3.3 FIELD QUALITY

- .1 Timber which contain rot, splits exposing untreated wood, excessive wane, or timbers which cannot be fastened in the work so as to be structurally sound are unacceptable.
- .2 The Departmental Representative reserves the right to carry out field testing of treated timber for penetration and retention of preservative. Timber not meeting the requirements of the specification may be rejected for use under the contract.