

PART 1 - GENERAL

1.1 REFERENCES

- .1 American Concrete Institute (ACI)
  - .1 SP-66-04, ACI Detailing Manual 2004.
- .2 ASTM International
  - .1 ASTM A1064/A1064M-17, Standard Specification for Steel Wire and Welded Wire Reinforcement, Plan and Deformed, for Concrete.
- .3 CSA International
  - .1 CSA-A23.1-14/A23.2-14, Concrete Materials and Methods of Concrete Construction/Test Methods and Standard Practices for Concrete.
  - .2 CAN/CSA-A23.3-14, Design of Concrete Structures.
  - .3 CSA-G30.18-09, Carbon Steel Bars for Concrete Reinforcement.
  - .4 CSA-G40.20/G40.21-04-13, General Requirements for Rolled or Welded Structural Quality Steel/Structural Quality Steel.
- .4 Reinforcing Steel Institute of Canada (RSIC)
  - .1 RSIC-2004, Reinforcing Steel Manual of Standard Practice.

1.2 ACTION AND INFORMATIONAL SUBMITTALS

- .1 Submit in accordance with Section 01 33 00 - Submittal Procedures.
- .2 Prepare reinforcement drawings in accordance with RSIC Manual of Standard Practice and SP-66.
- .3 Shop Drawings:
  - .1 Submit drawings stamped and signed by professional engineer registered or licensed in Province of Newfoundland and Labrador, Canada.
    - .1 Indicate placing of reinforcement and:
      - .1 Bar bending details.
      - .2 Lists.
      - .3 Quantities of reinforcement.

1.2 ACTION AND  
INFORMATIONAL  
SUBMITTALS  
(Cont'd)

- .3 Shop Drawings: (Cont'd)
- .1 (Cont'd)
- .1 (Cont'd)
- .4 Sizes, spacings, locations of reinforcement and mechanical splices if approved by Departmental Representative, with identifying code marks to permit correct placement without reference to structural drawings.
- .5 Indicate sizes, spacings and locations of chairs, spacers and hangers.
- .2 Detail lap lengths and bar development lengths to CAN/CSA-A23.3, unless otherwise indicated.
- .1 Provide type B tension lap splices unless otherwise indicated.

1.3 QUALITY  
ASSURANCE

- .1 Submit in accordance with Section 01 45 00 - Quality Control and as described in PART 2 - SOURCE QUALITY CONTROL.
- .1 Mill Test Report: upon request, provide Departmental Representative with certified copy of mill test report of reinforcing steel.
- .2 Upon request submit in writing to Departmental Representative proposed source of reinforcement material to be supplied.

1.4 DELIVERY,  
STORAGE AND  
HANDLING

- .1 Deliver, store and handle materials in accordance with Section 01 61 00 - Common Product Requirements and with manufacturer's written instructions.
- .2 Delivery and Acceptance Requirements: deliver materials to site in original factory packaging, labelled with manufacturer's name and address.
- .3 Storage and Handling Requirements:
- .1 Store materials off ground in dry location and in accordance with manufacturer's recommendations in clean, dry, well-ventilated area.
- .2 Replace defective or damaged materials with new.

1.4 DELIVERY,  
STORAGE AND  
HANDLING  
(Cont'd)  
PART 2 - PRODUCTS

- .4 Develop Construction Waste Management Plan related to Work of this Section and in accordance with Section 01 35 21 - LEED Requirements.

2.1 MATERIALS

- .1 Substitute different size bars only if permitted in writing by Departmental Representative.
- .2 Reinforcing steel: billet steel, grade 400 deformed bars to CSA-G30.18, unless indicated otherwise.
- .3 Cold-drawn annealed steel wire ties: to ASTM A 82/A 82M.
- .4 Deformed steel wire for concrete reinforcement: to ASTM A1064/A1064M.
- .5 Welded steel wire fabric: to ASTM A1064/A1064M.  
.1 Provide in flat sheets only.
- .6 Chairs, bolsters, bar supports, spacers: to CSA-A23.1/A23.2.
- .7 Mechanical splices: subject to approval of Departmental Representative.
- .8 Plain round bars: to CSA-G40.20/G40.21.

2.2 FABRICATION

- .1 Fabricate reinforcing steel in accordance with CSA-A23.1/A23.2, SP-66 and Reinforcing Steel Manual of Standard Practice by the Reinforcing Steel Institute of Canada.  
.1 SP-66 unless indicated otherwise.
- .2 Obtain Departmental Representative's written approval for locations of reinforcement splices other than those shown on placing drawings.
- .3 Ship bundles of bar reinforcement, clearly identified in accordance with bar bending details and lists.

- 2.3 SOURCE QUALITY CONTROL
- .1 Upon request, provide Departmental Representative with certified copy of mill test report of reinforcing steel, showing physical and chemical analysis.
  - .2 Upon request inform Departmental Representative of proposed source of material to be supplied.

PART 3 - EXECUTION

- 3.1 FIELD BENDING
- .1 Do not field bend or field weld reinforcement except where indicated or authorized by Departmental Representative.
  - .2 When field bending is authorized, bend without heat, applying slow and steady pressure.
  - .3 Replace bars, which develop cracks or splits.

- 3.2 PLACING REINFORCEMENT
- .1 Place reinforcing steel as indicated on placing drawings and in accordance with CSA-A23.1/A23.2.
  - .2 Use plain round bars as slip dowels in concrete.
    - .1 Paint portion of dowel intended to move within hardened concrete with one coat of asphalt paint.
    - .2 When paint is dry, apply thick even film of mineral lubricating grease.
  - .3 Prior to placing concrete, obtain Departmental Representative's approval of reinforcing material and placement.
  - .4 Ensure cover to reinforcement is maintained during concrete pour.

3.3 CLEANING

- .1 Progress Cleaning: clean in accordance with Section 01 74 11 - Cleaning.
  - .1 Leave Work area clean at end of each day.
- .2 Final Cleaning: upon completion remove surplus materials, rubbish, tools and equipment in accordance with Section 01 74 11 - Cleaning.
- .3 Waste Management: separate waste materials for reuse and recycling in accordance with Section 01 74 21 - Construction/Demolition Waste Management and Disposal and Section 01 35 21 - LEED Requirements.