

PART 1 - GENERAL

- 1.1 RELATED SECTIONS
- .1 Section 03 10 00 - Concrete Forming and Accessories.
 - .2 Section 03 30 00 - Cast-in-Place Concrete.
 - .3 Section 35 59 29 - Mooring Devices.
- 1.2 REFERENCES
- .1 American Concrete Institute (ACI)
 - .1 Latest edition of ACI 315, Manual of Engineering and Placing Drawings for Reinforced Concrete Structure.
 - .2 American National Standards Institute/American Concrete Institute (ANSI/ACI)
 - .1 Latest edition of ANSI/ACI 315, Details and Detailing of Concrete Reinforcement.
 - .3 Canadian Standards Association (CSA)
 - .1 Latest edition of CAN/CSA-A23.1, Concrete Materials and Methods of Concrete Construction.
 - .2 Latest edition of CSA-A23.3, Design of Concrete Structures for Buildings.
 - .3 Latest edition of CSA G30.3, Cold Drawn Steel Wire for Concrete Reinforcement.
 - .4 Latest edition of CSA G30.5, Welded Steel Wire Fabric for Concrete Reinforcement.
 - .5 Latest edition of CSA G30.14, Deformed Steel Wire for Concrete Reinforcement.
 - .6 Latest edition of CSA G30.15, Welded Deformed Steel Wire Fabric for Concrete Reinforcement.
 - .7 Latest edition of CAN/CSA-G30.18, Billet-Steel Bars for Concrete Reinforcement.

- .8 Latest edition of CAN/CSA-G40.21, Structural Quality Steels.
- .9 Latest edition of CAN/CSA-G164, Hot Dip Galvanizing of Irregularly Shaped Articles.
- .10 Latest edition of CSA W186, Welding of Reinforcing Bars in Reinforced Concrete Construction.

1.3 SHOP DRAWINGS

- .1 Submit shop drawings including placing of reinforcement in accordance with Section 01 33 00 - Submittal Procedures.
- .2 Indicate on shop drawings, bar bending details, lists, quantities of reinforcement, sizes, spacings, locations of reinforcement and mechanical splices if approved by Departmental Representative, with identifying code marks to permit correct placement without reference to structural drawings. Indicate sizes, spacings and locations of chairs, spacers and hangers. Prepare reinforcement drawings in accordance with Reinforcing Steel Manual of Standard Practice - by Reinforcing Steel Institute of Canada. ANSI/ACI 315 and ACI 315R, Manual of Engineering and Placing Drawings for Reinforced Concrete Structure.

1.4 WASTE MANAGEMENT AND DISPOSAL

- .1 Separate and recycle waste materials in accordance with Section 01 74 21 - Construction/Demolition Waste Management and Disposal and the Waste Reduction Workplan.

PART 2 - PRODUCTS

2.1 MATERIALS

- .1 Substitute different size bars only if permitted in writing by Departmental Representative.
- .2 Reinforcing steel: billet steel, grade 400, deformed bars to CAN/CSA-G30.18, unless indicated otherwise.
- .3 Reinforcing steel: weldable low alloy steel deformed bars to CAN/CSA-30.18.
- .4 Cold-drawn annealed steel wire ties: to CSA G30.3.
- .5 Welded steel wire fabric: to CSA G30.5. Provide in flat sheets only.
- .6 Chairs, bolsters, bar supports, spacers: to CAN/CSA-A23.1.
- .7 Mechanical splices: subject to approval of Departmental Representative.

2.2 FABRICATION

- .1 Fabricate reinforcing steel in accordance with CAN/CSA-A23.1, ANSI/ACI 315, and Reinforcing Steel Manual of Standard Practice by the Reinforcing Steel Institute of Canada. ACI 315R, Manual of Engineering and Placing Drawings for Reinforced Concrete Structures unless indicated otherwise.
- .2 Obtain Departmental Representative's approval for locations of reinforcement splices other than those shown on placing drawings.
- .3 Upon approval of Departmental Representative, weld reinforcement in accordance with CSA W186.

- .4 Ship bundles of bar reinforcement, clearly identified in accordance with bar bending details and lists.

2.3 SOURCE QUALITY CONTROL

- .1 Provide Departmental Representative with certified copy of mill test report of reinforcing steel, showing physical and chemical analysis, minimum 2 weeks prior to commencing reinforcing work.
- .2 Upon request inform Departmental Representative of proposed source of material to be supplied.

PART 3 - EXECUTION

3.1 FIELD BENDING

- .1 Do not field bend or field weld reinforcement except where indicated or authorized by Departmental Representative.
- .2 When field bending is authorized, bend without heat, applying a slow and steady pressure.
- .3 Replace bars which develop cracks or splits.

3.2 PLACING REINFORCEMENT

- .1 Place reinforcing steel as indicated on reviewed placing drawings and in accordance with CAN/CSA-A23.1.
- .2 Use approved type chairs to locate the reinforcing steel at the proper grade.
- .3 Tie reinforcement where spacing in each direction is:
 - .1 Less than 300mm: tie at alternate intersections.
 - .2 300mm or more: tie at each intersection.

- .4 Prior to placing concrete, obtain Departmental Representative's approval of reinforcing material and placement.
- .5 Ensure cover to reinforcement is maintained during concrete pour.

3.3 CLEANING

- .1 Clean reinforcing before placing concrete to CAN/CSA-A23.1.

END OF SECTION