

**The following changes in the bid documents are effective immediately. This addendum will form part of the contract documents.**

**SECTION: 03 30 00 – CAST IN PLACE CONCRETE**

Part 3 – EXECUTION

3.1 GENERAL

Add of the following:

- .12 Abrasive blast cleaning shall conform to Ontario Provincial Standard Specifications, OPSS.MUNI 929

**SECTION: 35 59 14 – MISCELLANEOUS METALS**

Part 2 – PRODUCTS

2.1 MATERIALS

- .4 Delete in its entirety

Replace with:

Paint for general steel components meeting the following requirements.

- .1 Marine grade, ultra-durable, solvent-free, epoxy based coating with solids content of 98% ± 2%. Where finish colour is unavailable in epoxy based systems, a polyurethane top coat may be substituted. Dry Film Thickness: 2 coats x 2-3 mils each. Finish colour shall be dark Grey for bollards and Yellow for ladders.
- .2 For pile caps, shop prime and field coat top and side exposed surfaces, after installation, with polyurethane top coat. Dry Film Thickness: 2-3 mils. Finish colour shall be yellow.
- .3 Surface profile for shop coating abrasive blasting to SSPC-SP10 with 3 to 4 mils surface profile.