

The following changes in the bid documents are effective immediately. This addendum will form part of the contract documents.

Section 35 59 14 – Miscellaneous Metals

Part 1

1.1 Specification Section 1.4

.1 Refer to article

.1 Add Section 1.4.3 with the following:

The Master Painters Institute (MPI): Exterior Structural Steel and Metal Fabrications, 07.

- .1 EXT 5.1G, Polyurethane, Pigmented (over epoxy zinc rich primer and high build epoxy).

Part 2

1.2 Specification Section 2.1

.1 Refer to article

.1 Delete Section 2.1.4 in its entirety.

.2 Replace with the following:

Paint for general steel components meeting the following requirements.

- .1 Primer: MPI EXT 5.1G, zinc rich epoxy primer. Maximum MPI E2 rating on VOC. Dry Film Thickness: 90µm (3.5 mils).
- .2 Epoxy intermediate coat: MPI EXT 5.1G, high build epoxy. Maximum MPI E2 rating on VOC. Dry Film Thickness: 100µm (4 mils).
- .3 Polyurethane top coat: MPI EXT 5.1G, aliphatic polyurethane. Maximum MPI E2 rating on VOC. Dry Film Thickness: 50µm (2 mils). Colour: traffic yellow
- .4 Shop prime all components.
- .5 Surface profile for shop coating abrasive blasting to SSPC-SP10 with 3 to 4 mils surface profile.