

1 General

1.1 RELATED REQUIREMENTS

- .1 Section 03 10 00 - Concrete Forming and Accessories.
- .2 Section 03 30 00 - Cast-in-Place Concrete.

1.2 REFERENCES

- .1 American Concrete Institute (ACI)
 - .1 ACI 315R-04, Manual of Engineering and Placing Drawings for Reinforced Concrete Structure.
 - .2 American National Standards Institute/American Concrete Institute (ANSI/ACI)
 - .1 ANSI/ACI 315-80, Details and Detailing of Concrete Reinforcement.
 - .3 American Society for Testing and Materials (ASTM)
 - .1 ASTM A 775/A 775M-076, Specification for Epoxy-Coated Reinforcing Steel Bars.
 - .4 Canadian Standards Association (CSA)
 - .1 CAN/CSA-A23.1-09, Concrete Materials and Methods of Concrete Construction.
 - .2 CAN3-A23.3-04, Design of Concrete Structures for Buildings.
 - .3 CSA G30.3-M1983 (R1998), Cold Drawn Steel Wire for Concrete Reinforcement.
 - .4 CSA G30.5-M1983 (R1998), Welded Steel Wire Fabric for Concrete Reinforcement.
 - .5 CSA G30.14-M1983 (R1998), Deformed Steel Wire for Concrete Reinforcement.
 - .6 CSA G30.15-M1983 (R1998), Welded Deformed Steel Wire Fabric for Concrete Reinforcement.
 - .7 CAN/CSA-G30.18-09, Billet-Steel Bars for Concrete Reinforcement.
 - .8 CAN/CSA-G40.21-04 (2009), Structural Quality Steels.
 - .9 CAN/CSA-G164-M92 (R2003), Hot Dip Galvanizing of Irregularly Shaped Articles.
 - .10 CSA W186-M1990 (R2007), Welding of Reinforcing Bars in Reinforced Concrete Construction.

1.3 SOURCE QUALITY CONTROL

- .1 Upon request, provide Departmental Representative with certified copy of mill test report of reinforcing steel, showing physical and chemical analysis, minimum 4 weeks prior to commencing reinforcing work.
- .2 Upon request inform Departmental Representative of proposed source of material to be supplied.

1.4 SHOP DRAWINGS

- .1 Submit shop drawings including placing of reinforcement in accordance with Section 01 33 00 - Submittal Procedures.
- .2 Indicate on shop drawings, bar bending details, lists, quantities of reinforcement, sizes, spacings, locations of reinforcement and mechanical splices if approved by Departmental Representative, with identifying code marks to permit correct placement without reference to structural drawings. Indicate sizes, spacings and locations of chairs, spacers and hangers. Prepare reinforcement drawings in accordance with Reinforcing Steel Manual of Standard Practice - by Reinforcing Steel Institute of Canada, ANSI/ACI 315 and ACI 315R, Manual of Engineering and Placing Drawings for Reinforced Concrete Structure.

- .3 Detail lap lengths and bar development lengths to CAN3-A23.3, unless otherwise indicated. Provide type A tension lap splices where indicated.
- .4 Each drawing submitted shall bear the signature and stamp of qualified professional engineer registered to practice in Newfoundland & Labrador.

1.5 WASTE MANAGEMENT AND DISPOSAL

- .1 Collect and separate for disposal waste material generated by this Section.
- .2 Place in appropriate on-site bins in accordance with Waste Management Plan.
- .3 A clean worksite is mandatory at all times. Failure to maintain the site in a clean, safe condition shall result in the Departmental Representative initiating a clean-up and related costs being deducted from progress claims.

2 Products

2.1 MATERIALS

- .1 Substitute different size bars only if permitted in writing by Departmental Representative.
- .2 Reinforcing steel: billet steel, grade 400, deformed bars to CAN/CSA-G30.18, unless indicated otherwise.
- .3 Cold-drawn annealed steel wire ties: to CSA G30.3.
- .4 Welded steel wire fabric: to CSA G30.5. Provide in flat sheets only.
 - .1 All 152 x 152 MW x 18.7 x 18.7
- .5 Chairs, bolsters, bar supports, spacers: to CAN/CSA-A23.1.
- .6 Mechanical splices: subject to approval of Departmental Representative.

2.2 FABRICATION

- .1 Fabricate reinforcing steel in accordance with CAN/CSA-A23.1, ANSI/ACI 315, and Reinforcing Steel Manual of Standard Practice by the Reinforcing Steel Institute of Canada. ACI 315R, Manual of Engineering and Placing Drawings for Reinforced Concrete Structures unless indicated otherwise.
- .2 Obtain Departmental Representative's approval for locations of reinforcement splices other than those shown on placing drawings.
- .3 Upon approval of Departmental Representative, weld reinforcement in accordance with CSA W186.
- .4 Ship bundles of bar reinforcement, clearly identified in accordance with bar bending details and lists.

3 Execution

3.1 FIELD BENDING

- .1 Do not field bend or field weld reinforcement except where indicated or authorized by Departmental Representative.
- .2 When field bending is authorized, bend without heat, applying a slow and steady pressure.
- .3 Replace bars which develop cracks or splits.

3.2 PLACING REINFORCEMENT

- .1 Place reinforcing steel as indicated on reviewed placing drawings and in accordance with CAN/CSA-A23.1.
 - .2 Use plain round bars as slip dowels in concrete. Paint portion of dowel intended to move within hardened concrete with one coat of asphalt paint. When paint is dry, apply a thick even film of mineral lubricating grease.
 - .3 Prior to placing concrete, obtain Departmental Representative's approval of reinforcing material and placement.
-

- .4 Ensure cover to reinforcement is maintained during concrete pour.
- .5 Protect epoxy coated portions of bars with covering during transportation and handling.
- .6 Provide concrete half-bricks to support welded wire mesh in proper position in floor slabs during placing of concrete.
- .7 Provide 20mm dowels into thickened concrete slabs at 1200mm on center or as noted on drawings for all masonry load bearing walls.

3.3 FIELD TOUCH-UP

- .1 Touch up damaged and cut ends of epoxy coated or galvanized reinforcing steel with compatible finish to provide continuous coating.

END OF SECTION
