

PART 1 - GENERAL

- 1.1 SUMMARY .1 This method covers measurement of loss of Marshall Stability resulting from action of water on compacted asphalt paving mixtures containing penetration grade asphalt cement.
- .2 Numerical index of retained stability is obtained by comparing stability of specimens determined in accordance with usual Marshall procedures with stability of specimens that have been immersed in water for prescribed period.
- 1.2 RELATED SECTIONS .1 Section 32 12 16 - Asphalt Paving.
- 1.3 REFERENCES .1 American Association of State Highway and Transportation Officials (AASHTO)
.1 AASHTO T245-97-UL-2004, Resistance to Plastic Flow of Bituminous Mixtures Using Marshall Apparatus.

PART 2 - PRODUCTS

- 2.1 MATERIALS .1 Representative samples of each asphalt paving mixture proposed for use on Project.
- 2.2 EQUIPMENT .1 One or more water baths with automatic controls for immersing specimens. Baths normally used for Marshall Immersion Test are suitable for test.
- .2 Scale and water bath with suitable accessory equipment for weighing test specimens in air and in water to determine their densities.
- .3 Flat transfer plates of glass or metal. Keep 1 plate under each specimen during immersion period and during subsequent handling, except when weighing and testing, to prevent breakage or distortion of specimens.
-

- 2.2 EQUIPMENT .4 Apparatus required to conduct Marshall Immersion
(Cont'd) Test.

PART 3 - EXECUTION

- 3.1 PREPARATION .1 Prepare at least 8 specimens for each test with
hand-operated hammer, in accordance with AASHTO
T245-97-UL, except where specified otherwise.

- 3.2 TEST PROCEDURE .1 Do Marshall testing in accordance with AASHTO
T245-97-UL, except where specified otherwise.
- .2 Weigh each specimen in air and in water. Weigh in
water as rapidly as possible to minimize
absorption.
- .3 Calculate specific gravity of each specimen as
follows:
.1 Specific Gravity = $A / A-B$
.2 Where A = weight of specimen in air in grams
.3 B = weight of specimen in water in grams
- .4 Sort each set of 8 specimens into 2 groups of 4
specimens each so that average specific gravity of
specimens in group 1 is essentially same as that
of group 2.
- .5 Test group 1 specimens for Marshall stability.
Calculate S1 = Marshall stability of group 1
(average).
- .6 Immerse group 2 specimens in water for 24 hours at
60 degrees C, then test immediately for Marshall
stability. Calculate S2 = Marshall stability of
group 2 (average).

- 3.3 TEST REPORT .1 Report test results to Departmental
Representative.
- .2 Report numerical index of retained stability as
resistance of asphaltic paving mixtures to
detrimental effect of water, expressed as
percentage of original stability retained after
immersion period.
- .3 Calculate index as follows:
-

Wharf Reconstruction
Trout River, NL
723199

MARSHALL IMMERSION TEST FOR
BITUMEN

Section 32 12 10
Page 3
May 2021

3.3 TEST REPORT
(Cont'd)

.3

(Cont'd)

.1 Index of Retained Stability = $S_2 / S_1 \times 100$.