

PART 1 - GENERAL

- | | | |
|------------------------------|----|---|
| <u>1.1 REFERENCES</u> | .1 | Health Canada/Workplace Hazardous Materials Information System (WHMIS)
.1 Material Safety Data Sheets (MSDS). |
| | .2 | The Master Painters Institute (MPI)
.1 Maintenance Repainting Manual 2004, Master Painters Institute (MPI), including Identifiers, Evaluation, Systems, Preparation and Approved Product List. |
| | .3 | National Fire Code of Canada. |
| | .4 | Test Method for Measuring Total Volatile Organic Compound Content of Consumer Products, Method 24 (for Surface Coatings) of the Environmental Protection Agency (EPA). |
| <u>1.2 QUALITY ASSURANCE</u> | .1 | Qualifications:
.1 Contractor: to have a minimum of five years proven satisfactory experience. When requested, provide list of last three comparable jobs including, job name and location, specifying authority, and project manager.
.2 Qualified journeypersons as defined by local jurisdiction to be engaged in painting work.
.3 Apprentices: may be employed provided they work under direct supervision of qualified journeypersons in accordance with applicable trade regulations. |
| | .2 | Conform to latest MPI requirements for exterior repainting work including cleaning, preparation and priming. |
| | .3 | Materials (primers, paints, coatings, varnishes, stains, lacquers, fillers, thinners, and solvents) to be in accordance with the latest edition of the MPI Approved Product List and to be from a single manufacturer for each system used. |
-

- | | | |
|--|----|--|
| 1.2 QUALITY ASSURANCE
<u>(Cont'd)</u> | .4 | Paint materials such as linseed oil, shellac, and turpentine, to be the highest quality product of an approved manufacturer listed in MPI Maintenance Repainting Manual and shall be compatible with other coating materials as required. |
| | .5 | Retain purchase orders, invoices and other documents to prove conformance with noted MPI requirements when requested by Departmental Representative. |
| 1.3 SCHEDULING
<u></u> | .1 | Schedule repainting operations to prevent disruption by other trades if applicable and by occupants in and about building. |
| 1.4 ACTION AND INFORMATIONAL SUBMITTALS
<u></u> | .1 | Provide submittals in accordance with Section 01 33 00 - Submittal Procedures. |
| | .2 | Provide samples in accordance with Section 01 33 00 - Submittal Procedures.
.1 Submit full range colour sample chips for review and selection. Indicate where colour availability is restricted. |
| | .3 | Provide product data and manufacturer's installation/application instructions for paints and coating products to be used. |
| 1.5 MAINTENANCE
<u></u> | .1 | Extra Materials:
.1 Provide maintenance materials in accordance with Section 01 78 00 - Closeout Submittals. |
| 1.6 DELIVERY, STORAGE AND HANDLING
<u></u> | .1 | Packing, shipping, handling and unloading:
.1 Deliver, store and handle materials in accordance with Section 01 61 00 - Common Product Requirements, supplemented as follows:
.1 Deliver and store materials in original containers, sealed, with labels intact.
.2 Labels to indicate: |
-

- 1.6 DELIVERY,
STORAGE AND
HANDLING
(Cont'd)
- .1 (Cont'd)
- .1 (Cont'd)
- .1 Manufacturer's name and address.
- .2 Type of paint or coating.
- .3 Compliance with applicable standard.
- .4 Colour number in accordance with established colour schedule.
- .3 Remove damaged, opened and rejected materials from site.
- .4 Store and handle in accordance with manufacturer's recommendations.
- .5 Store materials and equipment in secure, dry, well-ventilated area with temperature range between 7 degrees C to 30 degrees C. Store materials and supplies away from heat generating devices and sensitive products above minimum temperature as recommended by manufacturer.
- .6 Keep areas used for storage, cleaning and preparation, clean and orderly to approval of Departmental Representative. Upon completion of operations, return areas to clean condition to approval of Departmental Representative.
- .7 Remove paint materials from storage in quantities required for same day use.
- .8 Comply with requirements of Workplace Hazardous Materials Information System (WHMIS) regarding use, handling storage, and disposal of hazardous materials.
- .9 Fire Safety Requirements:
- .1 Provide one 9 kg Type ABC dry chemical fire extinguisher adjacent to storage area.
- .2 Store oily rags, waste products, empty containers and materials subject to spontaneous combustion in ULC approved, sealed containers and remove from site daily.
- .3 Handle, store, use and dispose of flammable and combustible materials in accordance with National Fire Code of Canada.
- .2 Waste Management and Disposal:
-

- | | |
|---|-------------|
| 1.6 DELIVERY,
STORAGE AND
HANDLING
<u>(Cont'd)</u> | .2 (Cont'd) |
|---|-------------|
- .1 Paint, stain and wood preservative finishes and related materials are hazardous products and are subject to regulations for disposal. Information on these controls can be obtained from Provincial Ministries of Environment and Regional levels of Government.
 - .2 Materials that cannot be reused must be treated as hazardous waste and disposed of in an appropriate manner.
 - .3 Place materials defined as hazardous or toxic waste, including used sealant and adhesive tubes and containers, in containers or areas designated for hazardous waste.
 - .4 To reduce the amount of contaminants entering waterways, sanitary/storm drain systems or into the ground the following procedures shall be strictly adhered to:
 - .1 Retain cleaning water for water-based materials to allow sediments to be filtered out. In no case shall equipment be cleaned using free draining water.
 - .2 Retain cleaners, thinners, solvents and excess paint and place in designated containers and ensure proper disposal.
 - .3 Return solvent and oil soaked rags used during painting operations for contaminant recovery, proper disposal, or appropriate cleaning and laundering.
 - .4 Dispose of contaminants in an approved legal manner in accordance with hazardous waste regulations.
 - .5 Empty paint cans are to be dry prior to disposal or recycling (where available).
 - .6 Close and seal tightly partly used cans of materials including sealant and adhesive containers and store protected in well ventilated fire-safe area at moderate temperature.
 - .5 Where paint recycling is available, collect waste paint by type and provide for delivery to recycling or collection facility.

- | | |
|--|--|
| 1.7 AMBIENT
CONDITIONS
<u> </u> | .1 Temperature, Humidity and Substrate Moisture
Content Levels: |
|--|--|
-

- 1.7 AMBIENT CONDITIONS
(Cont'd)
- .1 (Cont'd)
- .1 Unless specifically pre-approved by specifying body, Paint Inspection Agency and, applied product manufacturer.
- .2 Do not perform repainting work when:
- .1 Ambient air and substrate temperatures are below 10 degreesC.
- .2 Substrate temperature is over 32 degrees C unless paint is specifically formulated for application at high temperatures.
- .3 Substrate and ambient air temperatures are expected to fall outside paint manufacturer's prescribed limits.
- .4 Relative humidity is above 85% or when dew point is less than 3 degrees C variance between air/surface temperature.
- .5 Rain or snow is forecast to occur before paint has thoroughly cured.
- .6 It is foggy, misty, raining or snowing at site.
- .3 Conduct moisture tests using properly calibrated electronic Moisture Meter, except test existing painted concrete floors for moisture using simple "cover patch test" on failed areas.
- .4 Do not perform repainting work when maximum moisture content of substrate exceeds:
- .1 12% for concrete and masonry (clay and concrete brick/block).
- .2 15% for wood.
- .3 12% for stucco.
- .5 Test painted concrete, masonry and plaster surfaces for alkalinity as required.
- .2 Application Requirements:
- .1 Apply paint finish in areas where dust is no longer being generated by related construction operations or when wind conditions are such that airborne particles will affect quality of finished surface.
- .2 Apply paint to adequately prepared surfaces and to surfaces within moisture limits noted.
- .3 Apply paint when previous coat of paint is dry or adequately cured, unless otherwise pre-approved by specific coating manufacturer.
- .4 Apply paint finishes when conditions forecast for entire period of application fall within manufacturer's recommendations.
- .5 Do not apply paint when:
-

- | | | |
|--|-------------|---|
| 1.7 AMBIENT
CONDITIONS
<u>(Cont'd)</u> | .2 (Cont'd) | |
| | .5 (Cont'd) | |
| | .1 | Temperature is expected to drop below 10 degrees C before paint has thoroughly cured. |
| | .2 | Substrate and ambient air temperatures are expected to fall outside MPI or paint manufacturer's limits. |
| | .3 | Surface to be painted is wet, damp or frosted. |
| | .6 | Provide and maintain cover when paint must be applied in damp or cold weather. Heat substrates and surrounding air to comply with temperature and humidity conditions specified by manufacturer. Protect until paint is dry or until weather conditions are suitable. |
| | .7 | Schedule repainting operations such that surfaces exposed to direct, intense sunlight are scheduled for completion during early morning. |
| | .8 | Remove paint from areas which have been exposed to freezing, excess humidity, rain, snow or condensation. Prepare surface again and repaint. |

PART 2 - PRODUCTS

- | | | |
|----------------------|----|--|
| <u>2.1 MATERIALS</u> | .1 | Super spec HP Urethane Alkyd Gloss Enamel KP22 by Benjamin Moore. |
| | .2 | Super spec HP Alkyd Metal Primer by Benjamin Moore. |
| | .3 | Paint materials for repaint systems: products of single manufacturer. |
| | .4 | Paints, coatings, thinners, solvents, cleaners and other fluids used in repainting. |
| | .5 | Paints and coatings must be manufactured and transported in a manner that steps of processes, including disposal of waste products, will meet requirements of applicable governmental acts, by-laws and regulations including, for facilities located in Canada, Fisheries Act and Canadian Environmental Protection Act (CEPA). |

- | | | |
|---|----|---|
| <u>2.1 MATERIALS</u>
<u>(Cont'd)</u> | .6 | Paints and coatings must not be formulated or manufactured with formaldehyde, halogenated solvents, mercury, lead, cadmium, hexavalent chromium or their compounds. |
| <u>2.2 COLOURS</u> | .1 | Urethane alkyd gloss enamel. Provide shop drawings. |
| | .2 | Selection of colours will be from manufacturers full range of colours. |
| | .3 | Where specific products are available in restricted range of colours, selection will be based on limited range. |
| | .4 | First coat in two coat (Premium) repaint system to be tinted slightly lighter colour than top coat to show visible difference between coats. |
| <u>2.3 MIXING AND TINTING</u> | .1 | Alkyd metal primer. Provide shop drawings. |
| | .2 | Mix paste, powder or catalyzed paint mixes in accordance with manufacturer's written instructions. |
| | .3 | Where thinner is used, addition not to exceed paint manufacturer's recommendations. Do not use kerosene or such organic solvents to thin water-based paints. |
| | .4 | Re-mix paint in containers prior to and during application to ensure break-up of lumps, complete dispersion of settled pigment, and colour and gloss uniformity. |

PART 3 - EXECUTION

- | | | |
|--|----|---|
| <u>3.1 MANUFACTURER'S INSTRUCTIONS</u> | .1 | Compliance: comply with manufacturer's written recommendations or specifications, including product technical bulletins, handling, storage and installation instructions, and datasheets. |
|--|----|---|
-

3.2 EXAMINATION

- .1 Exterior repainting work.
- .2 Exterior surfaces requiring repainting:
inspected by both painting contractor who will notify Departmental Representative in writing of defects or problems, prior to commencing repainting work, or after surface preparation if unseen substrate damage is discovered.
- .3 Where "special" repainting or recoating system applications (i.e. elastomeric coatings) or non-MPI listed products or systems are to be used, paint or coating manufacturer to provide as part of work, certification of surfaces and conditions for specific paint or coating system application as well as on site supervision, inspection and approval of their paint or coating system application as required at no additional cost to Departmental Representative.

3.3 PREPARATION

- .1 Perform preparation and operations for exterior painting in accordance with MPI Maintenance Repainting requirements except where specified otherwise.
 - .2 Apply paint materials in accordance with paint manufacturer's written application instructions.
 - .3 Clean and prepare exterior surfaces to be repainted in accordance with MPI Maintenance Repainting Manual requirements. Refer to MPI Manual in regard to specific requirements and as follows:
 - .1 Remove dust, dirt, and surface debris by brushing, wiping with dry, clean cloths or compressed air.
 - .2 Wash surfaces with a biodegradable detergent (and bleach where applicable) and clean warm water using a stiff bristle brush to remove dirt, oil and surface contaminants.
 - .3 Rinse scrubbed surfaces with clean water until foreign matter is flushed from surface.
 - .4 Use trigger operated spray nozzles for water hoses.
 - .5 Allow surfaces to drain completely and to dry thoroughly.
-

3.3 PREPARATION
(Cont'd)

- .3 (Cont'd)
- .6 Use water-based cleaners in place of organic solvents where surfaces will be repainted using water based paints.
- .7 Many water-based paints cannot be removed with water once dried. However, minimize the use of kerosene or such organic solvents to clean up water-based paints.
- .4 Where required, pressure wash exterior surfaces prior to repainting in accordance with MPI standards for type of surfaces and recommended pressures to ensure complete removal of loose paint, stains, dirt, and foreign matter. This work to be carried out by qualified workers experienced in pressure water cleaning. Use of spray equipment such as water hose cleaning will not be considered satisfactory unless specified. Allow sufficient drying time and test surfaces using an electronic moisture meter before commencing work.
- .5 Clean metal surfaces to be repainted by removing rust, dirt, oil, grease and foreign substances in accordance with MPI requirements. Remove such contaminants from surfaces, pockets and corners to be repainted by brushing with clean brushes, blowing with clean dry compressed air, or brushing/vacuum cleaning as required.
- .6 Prevent contamination of cleaned surfaces by salts, acids, alkalis, corrosive chemicals, grease, oil and solvents before priming and between applications of remaining coats. Touch-up, spot prime, and apply primer, paint, or pre-treatment as soon as possible after cleaning and before deterioration occurs.
- .7 Sand and dust between coats as required to provide adequate adhesion for next coat and to remove defects from previously painting (e.g. runs, and sags) that are visible from distance up to 1000 mm.

3.4 EXISTING CONDITIONS

- .1 Prior to commencing work, examine site conditions and existing exterior substrates to be repainted and report in writing to Departmental Representative damages, defects, unsatisfactory or unfavourable conditions of surfaces that will adversely affect this work.
- .2 Conduct moisture testing of surfaces to be painted using a properly calibrated electronic moisture meter, except test concrete floors for moisture using a simple "cover patch test" and report findings to Departmental Representative. Maximum moisture content not to exceed specified limits.
- .3 No repainting work to commence until such adverse conditions and defects have been corrected and surfaces and conditions are acceptable to Painting Subcontractor and Inspection Agency.

3.5 PROTECTION

- .1 Protect existing building surfaces and adjacent structures from paint spatters, markings and other damage by suitable non-staining covers or masking. If damaged, clean and restore such surfaces as directed by Departmental Representative.
 - .2 Protect items that are permanently attached such as Fire Labels on doors and frames.
 - .3 Protect factory finished products and equipment.
 - .4 Protect general public and building occupants in and about the building.
 - .5 Removal of light fixtures, surface hardware on doors, and surface mounted equipment, fittings and fastenings to be done prior to undertaking painting operations. Store items and re-install after painting is completed.
 - .6 Move and cover exterior furniture and portable equipment as necessary to carry out painting operations. Replace as painting operations progress.
-

3.5 PROTECTION
(Cont'd)

.7 As painting operations progress, place "WET PAINT" signs in pedestrian and vehicle traffic areas to approval of Departmental Representative.

3.6 APPLICATION

.1 Apply paint by method that is best suited for substrate being repainted using brush, roller, air sprayer and/or airless sprayer. Conform to manufacturer's application instructions unless specified otherwise. In each case method of application to be as pre-approved by Departmental Representative before commencing work.

.2 Brush and Roller Application:

.1 Apply paint in a uniform layer using brush and/or roller of types suitable for application.

.2 Work paint into cracks, crevices and corners.

.3 Paint surfaces and corners not accessible to brush using spray, daubers and/or sheepskins. Paint surfaces and corners not accessible to roller using brush, daubers or sheepskins.

.4 Brush and/or roll out runs and sags, and over-lap marks. Rolled surfaces to be free of roller tracking and heavy stipple unless approved by Departmental Representative.

.5 Remove runs, sags and brush marks from finished work and repaint.

.3 Use dipping, sheepskins or daubers when no other method is practical in places of difficult access and when specifically authorized by Departmental Representative.

.4 Apply paint coats in a continuous manner and allow surfaces to dry and cure between coats for minimum time period as recommended by manufacturer. Minimum dry film thickness of coats not less than that recommended by manufacturer. Repaint thin spots or bare areas before next coat of paint is applied.

.5 Sand and dust between coats to remove visible defects.

- | | | |
|--|----|---|
| <u>3.6 APPLICATION
(Cont'd)</u> | .6 | Finish surfaces both above and below sight lines as specified for surrounding surfaces, including such surfaces as projecting ledges. |
| | .7 | Finish to doors include all edges including top and bottom edges. Surfaces concealed by door hardware be repainted unless otherwise pre-approved. |
| <u>3.7 MECHANICAL /
ELECTRICAL
EQUIPMENT</u> | .1 | Unless otherwise noted, repainting to include exposed to view/previously painted exterior mechanical and electrical equipment and components (panels, conduits, piping, hangers, and ductwork). |
| | .2 | Touch up scratches and marks and repaint such mechanical and electrical equipment and components with colour and finish to match existing finish unless otherwise noted or scheduled. |
| | .3 | Do not paint over name plates or instruction labels. |
| | .4 | Standard of Acceptance: when viewed using natural prevailing sunlight at peak period of the day (mid-day) on surface viewed, surfaces to indicate following:
.1 Walls: no defects visible from a distance of 1000 mm at 90 degrees to surface.
.2 Soffits: no defects visible from grade at 45 degrees to surface.
.3 Final coat to exhibit uniformity of colour and sheen across full surface area. |
| <u>3.8 CLEANING</u> | .1 | Proceed in accordance with Section 01 74 11 - Cleaning. |
| | .2 | Remove paint where spilled, splashed, splattered or sprayed as work progresses using means and materials that are not detrimental to affected surfaces. |
| | .3 | Keep work area free from unnecessary accumulation of tools, equipment, surplus materials and debris. |
-

3.8 CLEANING
(Cont'd)

- .4 Remove combustible rubbish materials and empty paint cans each day and safely dispose of same in accordance with requirements of authorities having jurisdiction.
- .5 Clean equipment and dispose of wash water used for water borne materials, solvents used for oil based materials as well as cleaning and protective materials (e.g. rags, drop cloths, and masking papers), paints, thinners, paint removers/strippers in accordance with the safety requirements of authorities having jurisdiction and as specified.
- .6 Clean painting equipment in leak-proof containers that will permit particulate matter to settle out and be collected. Sediment remaining from cleaning operations to be disposed of in manner acceptable to authorities having jurisdiction.
- .7 Recycle paint and coatings in excess of repainting requirements as specified.

3.9 RESTORATION

- .1 Clean and re-install hardware items removed before undertaken painting operations.
- .2 Remove protective coverings and warning signs as soon as practical after operations cease.
- .3 Remove paint splashings on affected exposed surfaces. Remove smears and spatter immediately as operations progress, using compatible solvent.
- .4 Protect freshly completed surfaces from paint droppings and dust to approval of Departmental Representative. Avoid scuffing newly applied paint.
- .5 Restore areas used for storage, cleaning, mixing and handling of paint to clean condition as approved by Departmental Representative.